

CELANYL® B3 GF25 BK 9005

CELANYL®

General purpose grade for any technical use. Medium heat ageing resistance.

Product information

Resin Identification	PA6-GF25	ISO 1043
Part Marking Code	>PA6-GF25<	ISO 11469
Continuous Service Temperature	110 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	145/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.3 - 0.6	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	8500/4500	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	147/85	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.5/6	%	ISO 527-1/-2
Charpy impact strength, 23°C	48/>80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	7.5/11	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	180/-	MPa	ISO 2039-1
Poisson's ratio	0.34/0.36 ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	210/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	220/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10

Electrical properties

	dry/cond.		
Volume resistivity	>1E13/-	Ohm.m	IEC 62631-3-1
Comparative tracking index	575/-		IEC 60112

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.9/*	%	Sim. to ISO 62
Water absorption, 2mm	6.6/*	%	Sim. to ISO 62
Density	1310/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes	
Drying Temperature	80	°C
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.15	%
Melt Temperature Optimum	260	°C
Min. melt temperature	240	°C

CELANYL® B3 GF25 BK 9005

CELANYL®

Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat

Automotive

OEM
VW Group

STANDARD
VW 50134

ADDITIONAL INFORMATION

*Best Fitting Grade to PA6-6-A, Not Officially
Approved