

CELANYL® B3 GF30 GY 7035/E

CELANYL®

General purpose grade, suitable for any technical application, medium term heat ageing resistance.

Product information

Resin Identification	PA6-GF30	ISO 1043
Part Marking Code	>PA6-GF30<	ISO 11469
Continuous Service Temperature	105 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.4/-	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.6/-	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	9000/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	150/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3/-	%	ISO 527-1/-2
Flexural strength	220/-	MPa	ISO 178
Charpy impact strength, 23°C	60/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	10.5/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Temperature of deflection under load, 0.45 MPa	210/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10
Thickness tested	1.6/*	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.8/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.6/*	%	Sim. to ISO 62
Water absorption, 2mm	6.5/*	%	Sim. to ISO 62
Density	1370/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C

CELANYL® B3 GF30 GY 7035/E

CELANYL®

Min. mould temperature	60 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Heat stabilised or stable to heat