

CELANYL® B3 GF30 NC 1102

CELANYL®

General purpose grade, suitable for any technical application, medium term heat ageing resistance. Improved flowability.

Product information

Resin Identification	PA6-GF30	ISO 1043
Part Marking Code	>PA6-GF30<	ISO 11469
Continuous Service Temperature	95 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	145/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.2 - 0.6	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 1	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	9400/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	180/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.5/-	%	ISO 527-1/-2
Charpy notched impact strength, 23°C	13.5/-	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	16/-	kJ/m ²	ISO 180/1A
Poisson's ratio	0.34/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	210/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	220/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.8/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94

Electrical properties

	dry/cond.		
Volume resistivity	1E13/-	Ohm.m	IEC 62631-3-1
Surface resistivity	*/1E13	Ohm	IEC 62631-3-2
Comparative tracking index, 100 drops	525		IEC 60112

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.8/*	%	Sim. to ISO 62
Water absorption, 2mm	6.3/*	%	Sim. to ISO 62
Density	1340/-	kg/m ³	ISO 1183

CELANYL® B3 GF30 NC 1102

CELANYL®

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat, High Flow