

CELANYL® B3 H GF15 BK 9005/H

CELANYL®

PA6 for injection molding, 15% glass fiber reinforced, heat stabilized
 Car industry, Household appliances, Electrical devices.

Product information

Resin Identification	PA6-GF15	ISO 1043
Part Marking Code	>PA6-GF15<	ISO 11469
Continuous Service Temperature	120 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	145/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.5 - 0.9	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.9 - 1.3	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	5800/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	125/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.5/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	35/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	4.5/-	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	160/-	MPa	ISO 2039-1
Poisson's ratio	0.35/- ^[C]		
[C]: Calculated			

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	180/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	215/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.8/*	mm	IEC 60695-11-10
Glow Wire Flammability Index, 0.75mm	650/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	650/-	°C	IEC 60695-2-12

Electrical properties

	dry/cond.		
Volume resistivity	1E13/-	Ohm.m	IEC 62631-3-1
Surface resistivity	*/1E13	Ohm	IEC 62631-3-2
Comparative tracking index	550/-		IEC 60112

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.9/*	%	Sim. to ISO 62
Water absorption, 2mm	7.5/*	%	Sim. to ISO 62
Density	1240/-	kg/m ³	ISO 1183

CELANYL® B3 H GF15 BK 9005/H

CELANYL®

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C


Characteristics

Processing	Injection Moulding
Special characteristics	Heat stabilised or stable to heat

CELANYL® B3 H GF15 BK 9005/H

CELANYL®

Stress-strain



CELANYL® B3 H GF15 BK 9005/H

CELANYL®

Secant modulus-strain

