

CELANYL[®] B3 H GF15 NC 1102/2

CELANYL[®]

General purpose grade, suitable for any technical application.

Product information

Resin Identification	PA6-GF15	ISO 1043
Part Marking Code	>PA6-GF15<	ISO 11469

Rheological properties

Moulding shrinkage range, parallel	0.4 - 0.7 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.7 - 1 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	5600/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	125/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.6/-	%	ISO 527-1/-2
Flexural modulus	5000/-	MPa	ISO 178
Charpy impact strength, 23°C	50/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.5/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.35/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	195/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.9/*	%	Sim. to ISO 62
Water absorption, 2mm	7/*	%	Sim. to ISO 62
Density	1230/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

CELANYL® B3 H GF15 NC 1102/2

CELANYL®

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat