

# CELANYL® B3 W GB30 NC 1102

## CELANYL®

This compound is designed for easy injection molding processing. It is suitable for Automotive, Electrical and Electronic and Industrial & Consumer applications.

### Product information

Resin Identification	PA6-GB30	ISO 1043
Part Marking Code	>PA6-GB30<	ISO 11469

### Rheological properties

	dry/cond.		
Viscosity number	145/*	cm <sup>3</sup> /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.9 - 1.2	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.9 - 1.2	%	ISO 294-4, 2577

### Typical mechanical properties

	dry/cond.		
Tensile modulus	4300/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	70/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	5/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	30/-	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	3/-	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	3.2/-	kJ/m <sup>2</sup>	ISO 180/1A
Ball indentation hardness, H 961/30	170/-	MPa	ISO 2039-1
Poisson's ratio	0.36/- <sup>[C]</sup>		

[C]: Calculated

### Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3

### Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10
UL recognition	yes/*		UL 94

### Electrical properties

	dry/cond.		
Volume resistivity	1E13/-	Ohm.m	IEC 62631-3-1
Comparative tracking index	550/-		IEC 60112

### Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.8/*	%	Sim. to ISO 62
Water absorption, 2mm	6.3/*	%	Sim. to ISO 62
Density	1330/-	kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes	
Drying Temperature	80	°C
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.15	%
Melt Temperature Optimum	260	°C
Min. melt temperature	240	°C

# CELANYL® B3 W GB30 NC 1102

## CELANYL®

Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

### Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat, High Flow, Low Warp