

CELANYL® B3 W NC 1102/UV/N/1

CELANYL®

Product information

Resin Identification	PA6	ISO 1043
Part Marking Code	>PA6<	ISO 11469

Typical mechanical properties

Izod notched impact strength, 23 °C	4.8 kJ/m ²	ISO 180/1A
-------------------------------------	-----------------------	------------

Thermal properties

Temperature of deflection under load, 1.8 MPa	66 °C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	177 °C	ISO 75-1/-2

Physical/Other properties

Density	1130 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	235 °C
Max. melt temperature	270 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	50 °C
Max. mould temperature	100 °C

Characteristics

Processing	Injection Moulding
Special characteristics	U.V. stabilised or stable to weather, Heat stabilised or stable to heat, Low wear / Low friction