

FRIANYL® B3 GF25 X V0 (PRELIMINARY)

FRIANYL®

Designed for Electrical applications requiring self-extinguishing properties combined with good mechanical performances, this grade meets the most stringent safety requirements for insulating materials.

Product information

Resin Identification	PA6-GF30 FR(40)	ISO 1043
Part Marking Code	>PA6-GF30 FR(40)<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

Rheological properties

Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	9000/5000	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	130/80	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3/7	%	ISO 527-1/-2
Charpy impact strength, 23°C	60/>60	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	40/45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	8/14	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	6.5/7	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34/0.35 ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	220/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	190/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	210/*	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 10N	210	°C	ISO 306
Ball pressure test	175/-	°C	IEC 60695-10-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.4/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12
FMVSS Class	SE		ISO 3795 (FMVSS 302)

Electrical properties

	dry/cond.		
Volume resistivity	>1E13/-	Ohm.m	IEC 62631-3-1
Surface resistivity	*/1E13	Ohm	IEC 62631-3-2
Comparative tracking index, 100 drops	600		IEC 60112

FRIANYL® B3 GF25 X V0 (PRELIMINARY)

FRIANYL®

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.4 / *	%	Sim. to ISO 62
Water absorption, 2mm	4.8 / *	%	Sim. to ISO 62
Density	1370 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	90 °C


Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat

FRIANYL® B3 GF25 X V0 (PRELIMINARY)

FRIANYL®


Stress-strain (dry)



FRIANYL® B3 GF25 X V0 (PRELIMINARY)

FRIANYL®


Stress-strain (cond.)



FRIANYL® B3 GF25 X V0 (PRELIMINARY)

FRIANYL®

Secant modulus-strain (dry)



FRIANYL® B3 GF25 X V0 (PRELIMINARY)

FRIANYL®

Secant modulus-strain (cond.)

