

FRIANYL® B3 GF30 V0 GY 7035/L

FRIANYL®

Designed for Electrical applications requiring self-extinguishing properties combined with good mechanical performances, this grade meets the most stringent safety requirements for insulating materials.

Product information

Resin Identification	PA6-GF30FR(40)	ISO 1043
Part Marking Code	>PA6-GF30FR(40)<	ISO 11469
Continuous Service Temperature	120 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	140 / *	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.2 - 0.4	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.7 - 0.9	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	10100 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	110 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.8 / -	%	ISO 527-1/-2
Charpy impact strength, 23°C	36 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.5 / -	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	215 / -	MPa	ISO 2039-1
Poisson's ratio	0.34 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	205 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
Ball pressure test	175 / -	°C	IEC 60695-10-2

Flammability

	dry/cond.		
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Glow Wire Flammability Index, 0.75mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	775 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	800 / -	°C	IEC 60695-2-13
FMVSS Class	SE		ISO 3795 (FMVSS 302)
Railway classification	R22 / R24		EN 45545-2
Railway classification rating	HL3 / HL3		EN 45545-2

FRIANYL® B3 GF30 V0 GY 7035/L

FRIANYL®

Electrical properties

	dry/cond.		
Volume resistivity	1E13/-	Ohm.m	IEC 62631-3-1
Surface resistivity	*/1E15	Ohm	IEC 62631-3-2

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.4/*	%	Sim. to ISO 62
Water absorption, 2mm	4/*	%	Sim. to ISO 62
Density	1440/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	90 °C

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat