

# FRIANYL® B3 V0 BK 9005/O

## FRIANYL®

Designed for any electrical application that require self-extinguishing properties, excellent surface quality and flexibility of use.

### Product information

Resin Identification	PA6-FR(30)	ISO 1043
Part Marking Code	>PA6-FR(30)<	ISO 11469
Continuous Service Temperature	125 °C	IEC 60216-1

### Rheological properties

Moulding shrinkage range, parallel	1.1 - 1.5 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.1 - 1.5 %	ISO 294-4, 2577

### Typical mechanical properties

	dry/cond.		
Tensile modulus	3400/-	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	75/-	MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	3/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	40/-	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	3/-	kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.37/- <sup>[C]</sup>		
[C]: Calculated			

### Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	85/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	185/*	°C	ISO 75-1/-2

### Flammability

	dry/cond.		
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.4/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
FMVSS Class	SE		ISO 3795 (FMVSS 302)

### Electrical properties

	dry/cond.		
Comparative tracking index	600/-		IEC 60112

### Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2.3/*	%	Sim. to ISO 62
Water absorption, 2mm	7.8/*	%	Sim. to ISO 62
Density	1160/-	kg/m <sup>3</sup>	ISO 1183

# FRIANYL® B3 V0 BK 9005/O

FRIANYL®

## Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	245 °C
Min. melt temperature	235 °C
Max. melt temperature	260 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	90 °C

## Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat

## Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
VW Group	VW 50134	*Best Fitting Grade To PA6-1-A, Not Officially Approved