

FRIANYL® B3 V0 NC 1102/V

FRIANYL®

Designed for any electrical application that require self-extinguishing properties, excellent surface quality and flexibility of use.

Product information

Resin Identification	PA6-FR(30)	ISO 1043
Part Marking Code	>PA6-FR(30)<	ISO 11469
Continuous Service Temperature	125 °C	IEC 60216-1

Rheological properties

Moulding shrinkage range, parallel	1.1 - 1.5 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.1 - 1.5 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	3750/-	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	75/-	MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	7/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	48/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	3/-	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	140/-	MPa	ISO 2039-1
Poisson's ratio	0.36/- ^[C]		
[C]: Calculated			

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	70/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	180/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.4/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
FMVSS Class	SE		ISO 3795 (FMVSS 302)

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2.3/*	%	Sim. to ISO 62
Water absorption, 2mm	7.7/*	%	Sim. to ISO 62
Density	1160/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	245 °C
Min. melt temperature	235 °C

FRIANYL® B3 V0 NC 1102/V

FRIANYL®

Max. melt temperature	260 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	90 °C

Characteristics

Processing	Injection Moulding
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat

Automotive

OEM
VW Group

STANDARD
VW 50134

ADDITIONAL INFORMATION
*Best Fitting Grade To PA6-1-A, Not Officially
Approved