

ZYTEL® 73G20UV ECO-R 311 BLK1LM (DEVELOPMENTAL) NYLON RESIN

Zytel® 73G20UV ECO-R 311 BLK1LM incorporates 30% of post-industrial recycled content by weight in the finished product. It is a 20% Glass Reinforced, UV Stabilized and Laser-markable Polyamide 6.

Product information

Resin Identification	PA6-GF20	ISO 1043
Part Marking Code	>PA6-GF20<	ISO 11469
Continuous Service Temperature	90 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Melt volume-flow rate	20 / *	cm ³ /10min	ISO 1133
Temperature	230 / *	°C	
Load	5 / *	kg	
Viscosity number	140 / *	cm ³ /g	ISO 307, 1628

Typical mechanical properties

	dry/cond.		
Tensile modulus	7100 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	130 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3 / -	%	ISO 527-1/-2
Charpy impact strength, 23°C	40 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5 / -	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.35 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225 / *	°C	ISO 11357-1/-3

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.6 / *	%	Sim. to ISO 62
Water absorption, 2mm	6.9 / *	%	Sim. to ISO 62
Density	1280 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	250 °C
Min. melt temperature	235 °C
Max. melt temperature	280 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

ZYTEL® 73G20UV ECO-R 311 BLK1LM (DEVELOPMENTAL) NYLON RESIN

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Special characteristics	U.V. stabilised or stable to weather, Laser Markable
Sustainability	Recycled Content

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
VW Group	VW 50125	*Best Fitting Grade To PA6-5, Not Officially Approved