

# CELANYL® A2 GF33 BK 2000/UV/1

## CELANYL®

### Product information

Resin Identification	PA66-GF33	ISO 1043
Part Marking Code	>PA66-GF33<	ISO 11469

### Typical mechanical properties

	dry/cond.		
Izod notched impact strength, 23 °C	13/-	kJ/m <sup>2</sup>	ISO 180/1A

### Physical/Other properties

	dry/cond.		
Density	1390/-	kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C

### Characteristics

Processing	Injection Moulding
Special characteristics	U.V. stabilised or stable to weather