

CELANYL® A2 GF33 BK 9005/1

CELANYL®

Product information

Resin Identification	PA66-GF33	ISO 1043
Part Marking Code	>PA66-GF33<	ISO 11469

Typical mechanical properties

	dry/cond.		
Tensile modulus	12500/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	195/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.2/-	%	ISO 527-1/-2
Flexural modulus	11000/-	MPa	ISO 178
Flexural strength	290/-	MPa	ISO 178
Charpy notched impact strength, 23°C	10.2/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33/- ^[C]		

[C]: Calculated

Physical/Other properties

	dry/cond.		
Density	1390/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
------------	--------------------