

# CELANYL® A2 H J10 BK 9005/A

## CELANYL®

General purpose grade, suitable for any technical applications requiring medium impact resistance and flexibility. UL listed HB@0.75mm.

### Product information

Resin Identification	PA66-I	ISO 1043
Part Marking Code	>PA66-I<	ISO 11469
Continuous Service Temperature	120 °C	IEC 60216-1

### Rheological properties

Moulding shrinkage range, parallel	1.2 - 1.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.2 - 1.6 %	ISO 294-4, 2577

### Typical mechanical properties

	dry/cond.		
Tensile modulus	2200 / 1150 <sup>[C]</sup>	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	55 / 30 <sup>[C]</sup>	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	5 / 10 <sup>[C]</sup>	%	ISO 527-1/-2
Tensile strain at break, 50mm/min	30 / - <sup>[C]</sup>	%	ISO 527-1/-2
Flexural modulus	2000 / -	MPa	ISO 178
Flexural strength	75 / -	MPa	ISO 178
Charpy impact strength, 23°C	N / N <sup>[C]</sup>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	18 / N <sup>[C]</sup>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	16 / -	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -30°C	7.5 / -	kJ/m <sup>2</sup>	ISO 180/1A
Poisson's ratio	0.39 / 0.44 <sup>[C]</sup>		

[C]: Calculated

### Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	265 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	65 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	190 / *	°C	ISO 75-1/-2

### Flammability

	dry/cond.		
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.2 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94

### Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.2 / *	%	Sim. to ISO 62
Water absorption, 2mm	7.2 / *	%	Sim. to ISO 62
Density	1090 / -	kg/m <sup>3</sup>	ISO 1183

### Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	High impact or impact modified, Heat stabilised or stable to heat

# CELANYL® A2 H J10 BK 9005/A

## CELANYL®

### Automotive

OEM

VW Group

VW Group

STANDARD

VW 50127

VW 50133

ADDITIONAL INFORMATION

\*Best Fitting Grade To PA66-2, Not Officially  
Approved

\*Best Fitting Grade To PA66-2-A, Not Officially  
Approved