

CELANYL® A2 HH GF33 BK 9005/1A

CELANYL®

Product information

Resin Identification	PA66-GF33	ISO 1043
Part Marking Code	>PA66-GF33<	ISO 11469

Typical mechanical properties

	dry/cond.		
Tensile modulus	12200/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	185/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.3/-	%	ISO 527-1/-2
Flexural modulus	10800/-	MPa	ISO 178
Flexural strength	280/-	MPa	ISO 178
Charpy notched impact strength, 23°C	11.5/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Temperature of deflection under load, 1.8 MPa	250/*	°C	ISO 75-1/-2

Physical/Other properties

	dry/cond.		
Density	1390/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Heat stabilised or stable to heat