

# CELANYL® A2 WR GF30 NC 1102/2A

## CELANYL®

Designed for technical application requiring long term heat resistance packed with prime quality mechanical performances.

### Product information

Resin Identification	PA66-GF30	ISO 1043
Part Marking Code	>PA66-GF30<	ISO 11469
Continuous Service Temperature	115 °C	IEC 60216-1

### Rheological properties

Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9 %	ISO 294-4, 2577

### Typical mechanical properties

	dry/cond.		
Tensile modulus	9700/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	190/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3/-	%	ISO 527-1/-2
Flexural modulus	8800/-	MPa	ISO 178
Charpy impact strength, 23°C	80/-	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	11/-	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	12/-	kJ/m <sup>2</sup>	ISO 180/1A
Poisson's ratio	0.34/- <sup>[C]</sup>		

[C]: Calculated

### Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	265/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	250/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	260/*	°C	ISO 75-1/-2

### Flammability

	dry/cond.		
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.8/*	mm	IEC 60695-11-10

### Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.7/*	%	Sim. to ISO 62
Water absorption, 2mm	5.9/*	%	Sim. to ISO 62
Density	1360/-	kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C

# CELANYL® A2 WR GF30 NC 1102/2A

## CELANYL®

Min. mould temperature 70 °C  
Max. mould temperature 120 °C

### Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat, High Flow

### Chemical Media Resistance

#### Salt solutions

- ✓ Sodium Hypochlorite solution (10% by mass), 23°C

#### Symbols used:

- ✓ possibly resistant  
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation  
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).