

# CELANYL® A3 H GF30 NC 1102/2

## CELANYL®

Designed for technical application requiring medium term heat resistance, good surface quality and mechanical performances.

### Product information

Resin Identification	PA66-GF30	ISO 1043
Part Marking Code	>PA66-GF30<	ISO 11469

### Rheological properties

Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9 %	ISO 294-4, 2577

### Typical mechanical properties

	dry/cond.		
Tensile modulus	9500/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	190/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.5/-	%	ISO 527-1/-2
Flexural modulus	8800/-	MPa	ISO 178
Charpy impact strength, 23°C	85/-	kJ/m <sup>2</sup>	ISO 179/1eU
Izod notched impact strength, 23°C	12/-	kJ/m <sup>2</sup>	ISO 180/1A
Poisson's ratio	0.34/- <sup>[C]</sup>		
[C]: Calculated			

### Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	265/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	250/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	260/*	°C	ISO 75-1/-2

### Flammability

	dry/cond.		
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.8/*	mm	IEC 60695-11-10

### Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.7/*	%	Sim. to ISO 62
Water absorption, 2mm	5.9/*	%	Sim. to ISO 62
Density	1360/-	kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C

# CELANYL® A3 H GF30 NC 1102/2

## CELANYL®

Max. mould temperature 120 °C

### Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat