

CELANYL® A3 W J20 NC 1102/1A

CELANYL®

Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469

Typical mechanical properties

Tensile modulus	1900 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	50 MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	40 %	ISO 527-1/-2
Flexural modulus	1800 MPa	ISO 178
Flexural strength	65 MPa	ISO 178
Charpy notched impact strength, 23°C	80 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.41 ^[C]	

[C]: Calculated

Physical/Other properties

Density	1080 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	290 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	50 °C
Max. mould temperature	100 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Heat stabilised or stable to heat