

# CELSTRAN® PA66-GF30-07

## CELSTRAN® Long Fibre

30% Long Glass Reinforced, High Gloss, Nylon 66

### Product information

Resin Identification	PA66-LGF30	ISO 1043
Part Marking Code	>PA66-LGF30<	ISO 11469

### Typical mechanical properties

Tensile modulus	9500 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	160 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.9 %	ISO 527-1/-2
Flexural modulus	9000 MPa	ISO 178
Flexural strength	240 MPa	ISO 178
Charpy notched impact strength, 23°C	15 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.34 <sup>[C]</sup>	

[C]: Calculated

### Physical/Other properties

Density	1360 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C
Hold pressure range	50 - 100 MPa

### Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Nucleated
Special characteristics	Heat stabilised or stable to heat

### Additional information

Injection molding

### Preprocessing

PA6&PA66 drying requirements: 4 hrs. @80° C.  
A dehumidifier or desiccant dryer is recommended.

# CELSTRAN® PA66-GF30-07

CELSTRAN® Long Fibre

## Processing

Celstran can be processed on a standard injection molding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition, and 20% metering. A free flowing check ring assembly is recommended.

Melt Temp: 275-285°C.

Mold Temp: 85- 95°C.

## Processing Notes

## Pre-Drying

CELSTRAN PA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be  $\leq -30^{\circ}\text{C}$ . The time between drying and processing should be as short as possible.

## Storage

Note: Material can be over dried and may discolor.