

CELSTRAN® PA66-GF50-02 AD3007

CELSTRAN® Long Fibre

Material code according to ISO 1043-1: PA66

Heat stabilized Nylon 66 reinforced by 50 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long.

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

Product information

Resin Identification	PA66-LGF50	ISO 1043
Part Marking Code	>PA66-LGF50<	ISO 11469

Rheological properties

Viscosity number	131 cm ³ /g	ISO 307, 1628
------------------	------------------------	---------------

Typical mechanical properties

Tensile modulus	16400 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	260 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2 %	ISO 527-1/-2
Flexural modulus	15100 MPa	ISO 178
Flexural strength	410 MPa	ISO 178
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10°C/min	260 °C	ISO 11357-1/-3
-------------------------------	--------	----------------

Physical/Other properties

Density	1560 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C
Hold pressure range	50 - 100 MPa

CELSTRAN® PA66-GF50-02 AD3007

CELSTRAN® Long Fibre

Back pressure

3 MPa

Characteristics

Processing

Injection Moulding

Delivery form

Pellets

Special characteristics

Heat stabilised or stable to heat
