

# ECOMID® A J6 GF43 BK 9005/UV/1

## ECOMID®

### Product information

Resin Identification	PA66-GF43	ISO 1043
Part Marking Code	>PA66-GF43<	ISO 11469

### Typical mechanical properties

Izod notched impact strength, 23 °C	18 kJ/m <sup>2</sup>	ISO 180/1A
-------------------------------------	----------------------	------------

### Thermal properties

Temperature of deflection under load, 1.8 MPa	249 °C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	260 °C	ISO 75-1/-2

### Physical/Other properties

Density	1500 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	285 °C
Min. melt temperature	275 °C
Max. melt temperature	295 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C

### Characteristics

Processing	Injection Moulding
Special characteristics	High impact or impact modified, U.V. stabilised or stable to weather