

FRIANYL® A3 E GF30 V0 BK 9011

Polyamide 66 compound, 30% glass fiber reinforced, heat resistant, based on flame retardants halogen and red phosphorous free. Certified UL V0@0.4mm.

Designed for Electrical applications requiring self-extinguishing properties combined with good mechanical performances, low blooming and corrosion, this grade meets the most stringent safety requirements for insulating materials. Suitable for EV high voltage applications.

Product information

Part Marking Code >(PA66+PA6)-GF30 FR(40)< ISO 11469

Rheological properties

| | | |
|------------------------------------|------------------------|---------------------|
| Viscosity number | 140 cm ³ /g | ISO 307, 1157, 1628 |
| Moulding shrinkage range, parallel | 0.3 - 0.6 % | ISO 294-4, 2577 |
| Moulding shrinkage range, normal | 0.6 - 0.9 % | ISO 294-4, 2577 |

Typical mechanical properties

| | | |
|---------------------------------------|-------------------------|--------------|
| | dry/cond. | |
| Tensile Modulus | 10500/- MPa | ISO 527-1/-2 |
| Stress at break, 5mm/min | 110/- MPa | ISO 527-1/-2 |
| Strain at break, 5mm/min | 2/- % | ISO 527-1/-2 |
| Flexural Modulus | 11500/- MPa | ISO 178 |
| Flexural Strength | 190/- MPa | ISO 178 |
| Charpy impact strength, 23°C | 45/- kJ/m ² | ISO 179/1eU |
| Charpy impact strength, -30°C | 38/- kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 7.5/- kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 6/- kJ/m ² | ISO 179/1eA |

Thermal properties

| | | |
|-------------------------------|--------|----------------|
| Melting temperature, 10°C/min | 260 °C | ISO 11357-1/-3 |
|-------------------------------|--------|----------------|

Flammability

| | | |
|--------------------------------------|-----------|----------------------|
| Burning Behav. at 1.5mm nom. thickn. | V-0 class | UL 94 |
| Burning Behav. at thickness h | V-0 class | UL 94 |
| Thickness tested | 0.4 mm | UL 94 |
| UL recognition | yes | UL 94 |
| Glow Wire Flammability Index, 0.4mm | 960 °C | IEC 60695-2-12 |
| Glow Wire Flammability Index, 0.75mm | 960 °C | IEC 60695-2-12 |
| Glow Wire Flammability Index, 2mm | 960 °C | IEC 60695-2-12 |
| Glow Wire Flammability Index, 3mm | 960 °C | IEC 60695-2-12 |
| FMVSS Class | SE | ISO 3795 (FMVSS 302) |

FRIANYL® A3 E GF30 V0 BK 9011

Electrical properties

| | dry/cond. | | |
|----------------------------|-----------|-------|---------------|
| Volume resistivity | >1E13 /- | Ohm.m | IEC 62631-3-1 |
| Surface resistivity | >1E13 /- | Ohm | IEC 62631-3-2 |
| Electric strength | 45 /- | kV/mm | IEC 60243-1 |
| Comparative tracking index | Group I | | IEC 60112 |
| Comparative tracking index | PLC 0 /- | PLC | UL 746A |

Other properties

| | | |
|--------------------------|------------------------|----------------|
| Humidity absorption, 2mm | 1.3 % | Sim. to ISO 62 |
| Water absorption, 2mm | 4.2 % | Sim. to ISO 62 |
| Density | 1420 kg/m ³ | ISO 1183 |

Characteristics

| | |
|-----------|---|
| Additives | Flame retardant, Non-halogenated/Red phosphorous free flame retardant |
|-----------|---|

Additional information

| | |
|-------------------|--|
| Injection molding | The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team. |
|-------------------|--|

Processing Texts

| | |
|---------------------------------|--|
| Injection molding | The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team. |
| Injection molding Preprocessing | PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should |

FRIANYL® A3 E GF30 V0 BK 9011

have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90 °C using dehumidified air (dew point of -20 °C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Injection molding Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50 °C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80 °C in oven, up to four hours). This procedure can be useful to relax any internal stresses.
