

FRIANYL® A3 GF07 V2XI NC 1101/X

FRIANYL®

Designed for Electrical applications requiring self-extinguishing properties combined with ignition resistance, this grade meets the most stringent safety requirements for insulating materials for the household appliance industry.

Product information

Resin Identification	PA66-GF07 FR(16+72)	ISO 1043
Part Marking Code	>PA66-GF07 FR(16+72)<	ISO 11469
Continuous Service Temperature	120 °C	IEC 60216-1

Rheological properties

Moulding shrinkage range, parallel	0.7 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.8 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	4100/-	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	3.5/-	%	ISO 527-1/-2
Tensile stress at break, 5mm/min	85/-	MPa	ISO 527-1/-2
Flexural modulus	3700/-	MPa	ISO 178
Flexural strength	120/-	MPa	ISO 178
Izod notched impact strength, 23 °C	4.5/-	kJ/m ²	ISO 180/1A
Izod impact strength, 23 °C	30/-	kJ/m ²	ISO 180/1U
Poisson's ratio	0.36/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Temperature of deflection under load, 0.45 MPa	250/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at thickness h	V-1/*	class	IEC 60695-11-10
Thickness tested	3.2/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.4mm	850/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.75mm	850/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	875/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 0.4mm	875/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 3.0mm	900/-	°C	IEC 60695-2-13
FMVSS Class	SE		ISO 3795 (FMVSS 302)

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.2/*	%	Sim. to ISO 62
Water absorption, 2mm	6/*	%	Sim. to ISO 62
Density	1420/-	kg/m ³	ISO 1183

FRIANYL® A3 GF07 V2XI NC 1101/X

FRIANYL®

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	280 °C
Min. melt temperature	265 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	70 °C
Max. mould temperature	90 °C

Characteristics

Processing	Injection Moulding
Additives	Flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat