

FRIANYL® A3 GF30 V0 GY 7035

FRIANYL®

Designed for Electrical applications requiring self-extinguishing properties combined with good mechanical performances, this grade meets the most stringent safety requirements for insulating materials.

Product information

Resin Identification	PA66-GF30 FR(40)	ISO 1043
Part Marking Code	>PA66-GF30 FR(40)<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	140/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.3 - 0.5	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.8 - 1	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	9750/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	110/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	36/-	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	32/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5/-	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4/-	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	220/-	MPa	ISO 2039-1
Poisson's ratio	0.34/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	260/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	210/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	220/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Thickness tested	1.6/*	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.4/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	775/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	800/-	°C	IEC 60695-2-13

Electrical properties

	dry/cond.		
Volume resistivity	1E13/-	Ohm.m	IEC 62631-3-1
Comparative tracking index	600/-		IEC 60112

FRIANYL® A3 GF30 V0 GY 7035

FRIANYL®

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.5 / *	%	Sim. to ISO 62
Water absorption, 2mm	4 / *	%	Sim. to ISO 62
Density	1420 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	285 °C
Min. melt temperature	270 °C
Max. melt temperature	300 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	100 °C
Ejection temperature	199 °C


Characteristics

Processing	Injection Moulding
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant

FRIANYL® A3 GF30 V0 GY 7035

FRIANYL®


Creep modulus-time 23°C



FRIANYL® A3 GF30 V0 GY 7035

FRIANYL®


Creep strain-time 23°C



FRIANYL® A3 GF30 V0 GY 7035

FRIANYL®

Creep modulus-time 80°C



FRIANYL® A3 GF30 V0 GY 7035

FRIANYL®

Creep strain-time 80°C

