

FRIANYL® A3 RV0 BK 9005/SZ

FRIANYL®

Designed for Electrical applications requiring self-extinguishing properties combined with easy processability and good surface quality, this grade meets the most stringent safety requirements for insulating materials.

Product information

Resin Identification	PA66 FR(30)	ISO 1043
Part Marking Code	>PA66 FR(30)<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	135/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage, parallel	1.2/-	%	ISO 294-4, 2577
Moulding shrinkage range, parallel	1 - 1.4	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.2/-	%	ISO 294-4, 2577
Moulding shrinkage range, normal	1 - 1.4	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	3400/2000	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	70/45	MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	2.5/8	%	ISO 527-1/-2
Flexural modulus	3500/-	MPa	ISO 178
Flexural strength	110/-	MPa	ISO 178
Charpy impact strength, 23°C	35/>60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	3/5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	3/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.37/0.4 ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	265/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	85/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	185/*	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.4/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12

FRIANYL® A3 RV0 BK 9005/SZ

FRIANYL®

Electrical properties

Comparative tracking index, 100 drops	600	IEC 60112
---------------------------------------	-----	-----------

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2.2/*	%	Sim. to ISO 62
Water absorption, 2mm	7.9/*	%	Sim. to ISO 62
Density	1160/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	275 °C
Min. melt temperature	265 °C
Max. melt temperature	285 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	90 °C

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat