

FRIANYL® A3 RV0 BK 9011/O

FRIANYL®

Designed for Electrical applications requiring self-extinguishing properties combined with easy processability and good surface quality, this grade meets the most stringent safety requirements for insulating materials.

Product information

Resin Identification	(PA66+PA6) FR(30)	ISO 1043
Part Marking Code	>(PA66+PA6) FR(30)<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	120/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage, parallel	1.2/-	%	ISO 294-4, 2577
Moulding shrinkage range, parallel	1 - 1.4	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.2/-	%	ISO 294-4, 2577
Moulding shrinkage range, normal	1 - 1.4	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	3300/-	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	65/-	MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	2.5/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	30/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	2.7/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.37/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	260/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	80/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	190/*	°C	ISO 75-1/-2
Ball pressure test	175/-	°C	IEC 60695-10-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.25/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12

Electrical properties

	dry/cond.		
Volume resistivity	1E12/-	Ohm.m	IEC 62631-3-1
Comparative tracking index, 100 drops	600		IEC 60112

FRIANYL® A3 RV0 BK 9011/O

FRIANYL®

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2.1 / *	%	Sim. to ISO 62
Water absorption, 2mm	7.4 / *	%	Sim. to ISO 62
Density	1160 / -	kg/m ³	ISO 1183

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Stellantis	B62 0300 / 61/217E/214M/C4	Orange;01378_20_00621