

FRIANYL® A3 RV0

FRIANYL®

Designed for Electrical applications requiring self-extinguishing properties combined with easy processability and good surface quality, this grade meets the most stringent safety requirements for insulating materials.

Product information

Resin Identification	PA66-FR(30)	ISO 1043
Part Marking Code	>PA66-FR(30)<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	145/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage, parallel	1.2/-	%	ISO 294-4, 2577
Moulding shrinkage range, parallel	1 - 1.4	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.2/-	%	ISO 294-4, 2577
Moulding shrinkage range, normal	1 - 1.4	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	3500 / 1300	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	80 / 50	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	3.5 / -	%	ISO 527-1/-2
Tensile strain at break, 50mm/min	10 / >50	%	ISO 527-1/-2
Charpy impact strength, 23°C	50 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	3 / -	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.37 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	260/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	80/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	190/*	°C	ISO 75-1/-2
Ball pressure test	175/-	°C	IEC 60695-10-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.25/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12
FMVSS Class	SE		ISO 3795 (FMVSS 302)

Electrical properties

	dry/cond.		
Volume resistivity	1E12/-	Ohm.m	IEC 62631-3-1
Comparative tracking index, 100 drops	600		IEC 60112

FRIANYL® A3 RV0

FRIANYL®

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2.1 / *	%	Sim. to ISO 62
Water absorption, 2mm	7.4 / *	%	Sim. to ISO 62
Density	1160 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	275 °C
Min. melt temperature	265 °C
Max. melt temperature	285 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	90 °C
Ejection temperature	220 °C

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat


Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Stellantis	B62 0300 / 61/217E/214M/C4	01378_20_00621
VW Group	VW 50133	*Best Fitting Grade To PA66-1-A, Not Officially Approved

FRIANYL® A3 RV0

FRIANYL®


Stress-strain (dry)



FRIANYL® A3 RV0

FRIANYL®


Stress-strain (cond.)



FRIANYL® A3 RV0

FRIANYL®

Secant modulus-strain (dry)



FRIANYL® A3 RV0

FRIANYL®

Secant modulus-strain (cond.)

