

Zytel® 101L NC010

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 101L NC010 is a lubricated polyamide 66 resin for injection moulding.

Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469
ISO designation	ISO 16396-PA66,,M1G1NR,S14-030	

Rheological properties

	dry/cond.		
Viscosity number	150 ^[1] /*	cm ³ /g	ISO 307, 1628
Moulding shrinkage, parallel	1.4 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.4 / -	%	ISO 294-4, 2577

[1]: Sulfuric acid 96%

Typical mechanical properties

	dry/cond.		
Tensile modulus	3100 / 1400	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	82 / 55	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	4.5 / 25	%	ISO 527-1/-2
Nominal strain at break	25 / >50	%	ISO 527-1/-2
Tensile strain at break, 50mm/min	45 / -	%	ISO 527-1/-2
Flexural modulus	2800 / 1200	MPa	ISO 178
Flexural strength	90 / 54	MPa	ISO 178
Tensile creep modulus, 1h	* / 1400	MPa	ISO 899-1
Tensile creep modulus, 1000h	* / 820	MPa	ISO 899-1
Charpy impact strength, 23°C	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	400 / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.5 / 15	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.5 / 3	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	5.5 / 12	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C	5.5 / 3.0	kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	5.5 / 3.0	kJ/m ²	ISO 180/1A
Izod impact strength, 23°C	N / N	kJ/m ²	ISO 180/1U
Izod impact strength, -30°C	300 / N	kJ/m ²	ISO 180/1U
Hardness, Rockwell, M-scale	79 / 59		ISO 2039-2
Hardness, Rockwell, R-scale	121 / 108		ISO 2039-2

Zytel® 101L NC010

NYLON RESIN

Ball indentation hardness, H 358/30	- / 85	MPa	ISO 2039-1
Ball indentation hardness, H 961/30	180 / -	MPa	ISO 2039-1
Poisson's ratio	0.37 / 0.43		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	70 / 40	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	70 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	190 / *	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	240 / *	°C	ISO 306
Ball pressure test	240 / -	°C	IEC 60695-10-2
Coefficient of linear thermal expansion (CLTE), parallel	100 / *	E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	110 / *	E-6/K	ISO 11359-1/-2
Thermal conductivity, flow	0.24	W/(m K)	ISO 22007-2
Thermal conductivity of melt	0.16	W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	5E-8	m ² /s	ISO 22007-4
Specific heat capacity of melt	2790	J/(kg K)	ISO 22007-4
Specific heat capacity solid	1680	J/(kg K)	ISO 22007-4
RTI, electrical, 0.75mm	130	°C	UL 746B
RTI, electrical, 1.5mm	130	°C	UL 746B
RTI, electrical, 3.0mm	130	°C	UL 746B
RTI, electrical, 6mm	130	°C	UL 746B
RTI, impact, 0.75mm	75	°C	UL 746B
RTI, impact, 1.5mm	75	°C	UL 746B
RTI, impact, 3.0mm	75	°C	UL 746B
RTI, impact, 6mm	75	°C	UL 746B
RTI, strength, 0.75mm	85	°C	UL 746B
RTI, strength, 1.5mm	85 / *	°C	UL 746B
RTI, strength, 3.0mm	85	°C	UL 746B
RTI, strength, 6mm	85	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.71 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Oxygen index	28 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index, 0.75mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	725 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.5mm	750 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	800 / -	°C	IEC 60695-2-13
Glow Wire Temperature, No Flame, 1mm	805 / -	°C	IEC 60335-1
Glow Wire Temperature, No Flame, 1.5mm	775 / -	°C	IEC 60335-1

Zytel® 101L NC010

NYLON RESIN

Glow Wire Temperature, No Flame, 2mm FMVSS Class	700 / - DNI	°C	IEC 60335-1 ISO 3795 (FMVSS 302)
Electrical properties	dry/cond.		
Relative permittivity, 100Hz	3.8 / 11		IEC 62631-2-1
Relative permittivity, 1MHz	3.5 / 4		IEC 62631-2-1
Dissipation factor, 100Hz	80 / 2100	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	180 / 750	E-4	IEC 62631-2-1
Volume resistivity	1E12 / 1E10	Ohm.m	IEC 62631-3-1
Electric strength	32 / 28	kV/mm	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112
Comparative tracking index, 23°C	0 / -	PLC	UL 746A
Comparative tracking index M	475 / -		IEC 60112
Physical/Other properties	dry/cond.		
Humidity absorption, 2mm	2.6 / *	%	Sim. to ISO 62
Water absorption, 2mm	8.5 / *	%	Sim. to ISO 62
Water absorption, Immersion 24h	1.2 ^[2] / *	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183
Density of melt	970	kg/m ³	
[2]: 3mm wall thickness			
Film Properties	dry/cond.		
Strain at yield, parallel	4.5 / *	%	ISO 527-3
VDA Properties	dry/cond.		
Emission of organic compounds	10	µgC/g	VDA 277
Odour	3.5	class	VDA 270
Fogging, G-value (condensate)	0.4 / *	mg	ISO 6452
Injection			
Drying Recommended	yes		
Drying Temperature	80	°C	
Drying Time, Dehumidified Dryer	2 - 4	h	
Processing Moisture Content	≤0.2	%	
Melt Temperature Optimum	290	°C	
Min. melt temperature	280	°C	
Max. melt temperature	300	°C	
Screw tangential speed	≤0.4	m/s	
Mold Temperature Optimum	70	°C	
Min. mould temperature	50	°C	
Max. mould temperature	90	°C	
Hold pressure range	50 - 100	MPa	
Hold pressure time	4	s/mm	
Ejection temperature	202	°C	

Zytel® 101L NC010

NYLON RESIN

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent

Additional information

Injection molding	POSTPROCESSING
	Annealing: 30min at 200°C


Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
BMW	GS93016-PA66	
Hyundai	MS211-37 Type D	
Hyundai	MS211-46 Type E	
Mercedes-Benz	DBL5409.20 PA66	
Stellantis	B62 0300 / 61/212E/210M	CPN5308, CPN1938, 01378_22_03585;61/212E/210M*
Stellantis	MS.50017 / PA66.2800F.5I	CPN5308, CPN1938
Stellantis - Chrysler	MS.50017 / CPN-1938	Natural
Stellantis - Chrysler	MS.50017 / CPN-5308	Natural
VW Group	VW 50127 PA66-1	
VW Group	VW 50133 PA66-1-A	

Zytel® 101L NC010

NYLON RESIN


Viscosity-shear rate



Zytel® 101L NC010

NYLON RESIN


Shearstress-shear rate



Zytel® 101L NC010

NYLON RESIN


Dynamic Tensile modulus-temperature (dry)



Zytel® 101L NC010

NYLON RESIN


Stress-strain (dry)



Zytel® 101L NC010

NYLON RESIN


Stress-strain (cond.)



Zytel® 101L NC010

NYLON RESIN


Secant modulus-strain (dry)



Zytel® 101L NC010

NYLON RESIN


Secant modulus-strain (cond.)



Zytel® 101L NC010

NYLON RESIN


Stress-strain (isochronous) 23°C (cond.)



Zytel® 101L NC010

NYLON RESIN


Creep modulus-time 23°C (cond.)



Zytel® 101L NC010

NYLON RESIN


Stress-strain (isochronous) 60°C (cond.)



Zytel® 101L NC010

NYLON RESIN


Creep modulus-time 60°C (cond.)



Zytel® 101L NC010

NYLON RESIN


Stress-strain (isochronous) 90°C (cond.)



Zytel® 101L NC010

NYLON RESIN


Creep modulus-time 90°C (cond.)



Zytel® 101L NC010

NYLON RESIN


Tensile modulus-temperature (dry)



Zytel® 101L NC010

NYLON RESIN

Tensile modulus-temperature (cond.)



Zytel® 101L NC010

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C

Zytel® 101L NC010

NYLON RESIN

- ✓ Sodium Carbonate solution (20% by mass), 23 °C
- ✓ Sodium Carbonate solution (2% by mass), 23 °C
- ✗ Zinc Chloride solution (50% by mass), 23 °C

Other

- ✓ Ethyl Acetate, 23 °C
- ✗ Hydrogen peroxide, 23 °C
- ✗ DOT No. 4 Brake fluid, 130 °C
- ✗ Ethylene Glycol (50% by mass) in water, 108 °C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23 °C
- ✓ 50% Oleic acid + 50% Olive Oil, 23 °C
- ✓ Water, 23 °C
- ✗ Water, 90 °C
- ✗ Phenol solution (5% by mass), 23 °C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).