

Zytel® FGFE5171 NC010C

NYLON RESIN

Zytel® FGFE5171 NC010C is a 33% glass filled nylon 66 resin. It has been developed for consideration into applications such as parts for the food industry.

FOOD CONTACT

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from our representative.

Product information

Resin Identification	PA66-GF33	ISO 1043
Part Marking Code	>PA66-GF33<	ISO 11469
ISO designation	ISO 16396-PA66,GF33,M1GN,S14-100	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.3/-	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.9/-	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	10500/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	200/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.5/-	%	ISO 527-1/-2
Flexural modulus	9300/-	MPa	ISO 178
Flexural strength	290/-	MPa	ISO 178
Charpy notched impact strength, 23°C	10/-	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34/-		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	263/*	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	70/20	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	252/*	°C	ISO 75-1/-2
RTI, electrical, 0.75mm	130	°C	UL 746B
RTI, electrical, 1.5mm	130	°C	UL 746B
RTI, electrical, 3.0mm	130	°C	UL 746B
RTI, impact, 0.75mm	120	°C	UL 746B
RTI, impact, 1.5mm	120	°C	UL 746B
RTI, impact, 3.0mm	120	°C	UL 746B
RTI, strength, 0.75mm	130	°C	UL 746B
RTI, strength, 1.5mm	130/*	°C	UL 746B
RTI, strength, 3.0mm	130	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	HB/*	class	IEC 60695-11-10
Thickness tested	0.71/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94

Zytel® FGFE5171 NC010C

NYLON RESIN

FMVSS Class	B		ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80	mm/min	ISO 3795 (FMVSS 302)

Physical/Other properties

	dry/cond.		
Density	1390/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C
Hold pressure range	50 - 100 MPa
Hold pressure time	3 s/mm
Ejection temperature	210 °C

Characteristics

Processing	Injection Moulding
------------	--------------------