

Zytel® FR70M30V0 NC010

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® FR70M30V0 NC010 is a 30% mineral reinforced, flame retardant polyamide 66 resin for injection moulding.

Product information

Resin Identification	PA66-MD30FR(17)	ISO 1043
Part Marking Code	>PA66-MD30FR(17)<	ISO 11469
ISO designation	ISO 16396-PA66,MD30 FR(17),M1F1GNR,S14-060	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	1.0/-	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.0/-	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	6500/3500	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	73/50	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2/6	%	ISO 527-1/-2
Charpy impact strength, 23°C	20/30	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	20/19	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	2.5/3	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	2/2	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	2/2.5	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C	2.0/1.9	kJ/m ²	ISO 180/1A
Poisson's ratio	0.35/0.37		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	263/*	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	80/20	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	145/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	238/*	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	235/*	°C	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	64/*	E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	81/*	E-6/K	ISO 11359-1/-2
Thermal conductivity of melt	0.23	W/(m K)	ISO 22007-2
Specific heat capacity of melt	1700	J/(kg K)	ISO 22007-4

Zytel® FR70M30V0 NC010

NYLON RESIN

RTI, electrical, 0.75mm	105	°C	UL 746B
RTI, electrical, 1.5mm	120	°C	UL 746B
RTI, electrical, 3.0mm	120	°C	UL 746B
RTI, impact, 0.75mm	95	°C	UL 746B
RTI, impact, 1.5mm	105	°C	UL 746B
RTI, impact, 3.0mm	115	°C	UL 746B
RTI, strength, 0.75mm	105	°C	UL 746B
RTI, strength, 1.5mm	115/*	°C	UL 746B
RTI, strength, 3.0mm	115	°C	UL 746B

Flammability

		dry/cond.	
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	V-2/*	class	IEC 60695-11-10
Thickness tested	0.75/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Burning Behav. 5V at thickness h	5VA/*	class	IEC 60695-11-20
Thickness tested	1.5/*	mm	IEC 60695-11-20
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	800/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.0mm	800/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.5mm	800/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	800/-	°C	IEC 60695-2-13
FMVSS Class	DNI		ISO 3795 (FMVSS 302)

Electrical properties

		dry/cond.	
Relative permittivity, 100Hz	4.1/9.1		IEC 62631-2-1
Relative permittivity, 1MHz	3.7/4.2		IEC 62631-2-1
Dissipation factor, 100Hz	140/410	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	140/500	E-4	IEC 62631-2-1
Volume resistivity	>1E13/1E9	Ohm.m	IEC 62631-3-1
Surface resistivity	*/>1E15	Ohm	IEC 62631-3-2
Electric strength	40/33	kV/mm	IEC 60243-1
Comparative tracking index	325/-		IEC 60112

Physical/Other properties

		dry/cond.	
Humidity absorption, 2mm	1.3/*	%	Sim. to ISO 62
Water absorption, 2mm	4/*	%	Sim. to ISO 62
Density	1620/-	kg/m ³	ISO 1183
Density of melt	1400	kg/m ³	

Zytel® FR70M30V0 NC010

NYLON RESIN

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	290 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C
Hold pressure range	50 - 100 MPa
Hold pressure time	3 s/mm
Ejection temperature	210 °C


Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent, Flame retardant
Special characteristics	Flame retardant

Zytel® FR70M30V0 NC010

NYLON RESIN


Viscosity-shear rate



Zytel® FR70M30V0 NC010

NYLON RESIN


Shearstress-shear rate



Zytel® FR70M30V0 NC010

NYLON RESIN


Stress-strain (dry)



Zytel® FR70M30V0 NC010

NYLON RESIN


Stress-strain (cond.)



Zytel® FR70M30V0 NC010

NYLON RESIN


Secant modulus-strain (dry)



Zytel® FR70M30V0 NC010

NYLON RESIN

Secant modulus-strain (cond.)



Zytel® FR70M30V0 NC010

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✓ SAE 10W40 multigrade motor oil, 130°C
- ✓ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C

Zytel® FR70M30V0 NC010

NYLON RESIN

- ✓ Sodium Carbonate solution (20% by mass), 23 °C
- ✓ Sodium Carbonate solution (2% by mass), 23 °C
- ✗ Zinc Chloride solution (50% by mass), 23 °C

Other

- ✓ Ethyl Acetate, 23 °C
- ✗ Hydrogen peroxide, 23 °C
- ✓ DOT No. 4 Brake fluid, 130 °C
- ✓ Ethylene Glycol (50% by mass) in water, 108 °C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23 °C
- ✓ 50% Oleic acid + 50% Olive Oil, 23 °C
- ✓ Water, 23 °C
- ✗ Water, 90 °C
- ✗ Phenol solution (5% by mass), 23 °C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).