

CELSTRAN® PA66-GF50-0111P7.5/11

CELSTRAN® Long Fibre

Material code according to ISO 1043-1: PA66

Nylon 6.6/6 copolymer reinforced by 50 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 7.5 mm long.

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

Product information

| | | |
|----------------------|---------------|-----------|
| Resin Identification | PA666-LGF50 | ISO 1043 |
| Part Marking Code | >PA666-LGF50< | ISO 11469 |

Typical mechanical properties

| | dry/cond. | | |
|---------------------------------------|----------------------------|-------------------|--------------|
| Tensile modulus | 16400 / 11600 | MPa | ISO 527-1/-2 |
| Tensile stress at break, 5mm/min | 275 / 180 | MPa | ISO 527-1/-2 |
| Tensile strain at break, 5mm/min | 2.2 / 2.5 | % | ISO 527-1/-2 |
| Flexural modulus | 13500 / 11500 | MPa | ISO 178 |
| Flexural strength | 380 / 300 | MPa | ISO 178 |
| Flexural strain at failure | 3.2 / 4 | % | ISO 178 |
| Charpy impact strength, 23°C | 100 / 50 | kJ/m ² | ISO 179/1eU |
| Charpy impact strength, -30°C | 80 / - | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 40 / 36 | kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 42 / - | kJ/m ² | ISO 179/1eA |
| Poisson's ratio | 0.33 / 0.33 ^[C] | | |

[C]: Calculated

Thermal properties

| | dry/cond. | | |
|---|-----------|----|----------------|
| Melting temperature, 10°C/min | 240 / * | °C | ISO 11357-1/-3 |
| Temperature of deflection under load, 1.8 MPa | 235 / * | °C | ISO 75-1/-2 |
| Temperature of deflection under load, 8 MPa | 220 / * | °C | ISO 75-1/-2 |

Flammability

| | dry/cond. | | |
|--------------------------------------|-----------|-------|-----------------|
| Burning Behav. at 1.5mm nom. thickn. | HB / * | class | IEC 60695-11-10 |
| Thickness tested | 1.5 / * | mm | IEC 60695-11-10 |
| UL recognition | yes / * | | UL 94 |

Physical/Other properties

| | dry/cond. | | |
|---------|-----------|-------------------|----------|
| Density | 1560 / - | kg/m ³ | ISO 1183 |

CELSTRAN® PA66-GF50-0111P7.5/11

CELSTRAN® Long Fibre

Injection

Back pressure 3 MPa

Characteristics

| | |
|-------------------------|-----------------------------------|
| Processing | Injection Moulding |
| Delivery form | Pellets |
| Special characteristics | Heat stabilised or stable to heat |