

# CELANEX® 2002SW1

## CELANEX® PBT

Celanex 2002SW1 Natural is an unreinforced PTFE-modified PBT with improved friction, sliding, and wear properties.

### Product information

Resin Identification	PBT+PTFE	ISO 1043
Part Marking Code	>PBT+PTFE<	ISO 11469

### Rheological properties

Melt volume-flow rate	21 cm <sup>3</sup> /10min	ISO 1133
Temperature	250 °C	
Load	2.16 kg	
Moulding shrinkage range, parallel	1.7 - 2.1 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.9 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.7 - 2.1 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	2600 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	56 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	7 %	ISO 527-1/-2
Nominal strain at break	19 %	ISO 527-1/-2
Charpy notched impact strength, 23 °C	3.3 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.38 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10 °C/min	225 °C	ISO 11357-1/-3
Glass transition temperature, 10 °C/min	60 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	55 °C	ISO 75-1/-2
Vicat softening temperature, 50 °C/h 50N	190 °C	ISO 306

### Electrical properties

Comparative tracking index	600	IEC 60112
----------------------------	-----	-----------

### Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1340 kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Screw tangential speed	0.1 - 0.3 m/s
Mold Temperature Optimum	80 °C

# CELANEX® 2002SW1

## CELANEX® PBT

Min. mould temperature	60 °C
Max. mould temperature	130 °C
Ejection temperature	190 °C

### Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Special characteristics	Low wear / Low friction

### Additional information

Injection molding

### Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40 °F (-40 °C) at 250 °F (120 °C) for minimum 4 hours.

### Processing

Rear Temperature 450-470(230-240) deg F (deg C)  
 Center Temperature 460-480(235-250) deg F (deg C)  
 Front Temperature 470-500(240-260) deg F (deg C)  
 Nozzle Temperature 480-500(250-260) deg F (deg C)  
 Melt Temperature 460-500(235-260) deg F (deg C)  
 Mold Temperature 150-200(65-93) deg F (deg C)  
 Back Pressure 0-50 psi  
 Screw Speed Medium  
 Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Notes

### Pre-Drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40 °F (-40 °C) at 250 °F (120 °C) for minimum 4 hours.

### Storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.