

CELANEX® 2003-5

unfilled; medium-high flow; lubricated PBT grade

Celanex 2003-5 is a general purpose, unreinforced polybutylene terephthalate with a good balance of mechanical properties and processability for use in industrial and automotive applications. Celanex 2003-5 is a medium to high flow material that contains a small amount of an internal lubricant and nucleant.

Rheological properties

Melt volume-flow rate	40 cm ³ /10min	ISO 1133
Temperature	250 °C	
Load	2.16 kg	
Moulding shrinkage range, parallel	1.8 - 2.2 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.8 - 2.0 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	2700 MPa	ISO 527-1/-2
Yield stress, 50mm/min	60 MPa	ISO 527-1/-2
Yield strain, 50mm/min	4 %	ISO 527-1/-2
Nominal strain at break	15 %	ISO 527-1/-2
Flexural Modulus	2550 MPa	ISO 178
Flexural Strength	80 MPa	ISO 178
Charpy impact strength, 23°C	135 kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	130 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.5 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	60 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	60 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	160 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	190 °C	ISO 306
Coeff. of linear therm. expansion, parallel	110 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	HB class	UL 94
Thickness tested	0.80 mm	UL 94

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	0.45 %	Sim. to ISO 62
Density	1310 kg/m ³	ISO 1183

CELANEX® 2003-5

Injection

Drying Temperature	120 - 130 °C	
Drying Time, Dehumidified Dryer	4 h	
Processing Moisture Content	0.02 %	
Melt Temperature Optimum	250 °C	Internal
Max. mould temperature	65 - 90 °C	
Injection speed	medium-fast	

Characteristics

Additives	Release agent
-----------	---------------

Additional information

Injection molding	<p>Rear Temperature 450-470(230-240) deg F (deg C) Center Temperature 460-480(235-250) deg F (deg C) Front Temperature 470-500(240-260) deg F (deg C) Nozzle Temperature 480-500(250-260) deg F (deg C) Melt Temperature 460-500(235-260) deg F (deg C) Mold Temperature 150-200(65-93) deg F (deg C) Back Pressure 0-50 psi Screw Speed Medium Injection Speed Fast</p>
-------------------	--

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Texts

Pre-drying	To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.
Longer pre-drying times/storage	For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.
Injection molding	<p>Rear Temperature 450-470(230-240) deg F (deg C) Center Temperature 460-480(235-250) deg F (deg C) Front Temperature 470-500(240-260) deg F (deg C) Nozzle Temperature 480-500(250-260) deg F (deg C) Melt Temperature 460-500(235-260) deg F (deg C) Mold Temperature 150-200(65-93) deg F (deg C) Back Pressure 0-50 psi</p>

CELANEX® 2003-5

Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Injection molding Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for 4 hours.
