

# CELANEX® 2300 GV1/20T ED3002 BLACK

## CELANEX® PBT

General purpose, 20% glass fiber reinforced PBT grade, black color, lubricated and stabilized. Good mechanical strength and toughness.

### Product information

Resin Identification	PBT-GF20	ISO 1043
Part Marking Code	>PBT-GF20<	ISO 11469

### Rheological properties

Melt volume-flow rate	12 cm <sup>3</sup> /10min	ISO 1133
Temperature	250 °C	
Load	2.16 kg	

### Typical mechanical properties

Tensile modulus	7400 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	120 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.5 %	ISO 527-1/-2
Flexural modulus	7000 MPa	ISO 178
Flexural strength	190 MPa	ISO 178
Charpy notched impact strength, 23 °C	9.3 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23 °C	9.5 kJ/m <sup>2</sup>	ISO 180/1A
Poisson's ratio	0.35 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10 °C/min	225 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	206 °C	ISO 75-1/-2

### Physical/Other properties

Density	1450 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Screw tangential speed	0.1 - 0.3 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	130 °C

# CELANEX® 2300 GV1/20T ED3002 BLACK

## CELANEX® PBT

### Characteristics

Processing	Injection Moulding
Delivery form	Pellets

### Additional information

Injection molding

### Processing

Melt Temperature 260-270 °C  
Mold Temperature \*) 75-85 °C  
Maximum Barrel Residence Time \*\*) 5-10 min  
Injection Speed fast  
Peripheral screw speed max.0,3 m/sec  
Back Pressure 10-30 bar  
Injection Pressure 600-1000 bar  
Holding Pressure 400-800 bar  
Nozzle Design open design preferred

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided. For grades containing flame retardants, a maximum temperature of 265 °C should not be exceeded.

Celanese recommends only externally heated hot runner systems.

\*) For moulded parts with especially high requirements to the surface quality or dimensional stability, a mold temperature of up to 110 °C can be advantageous.

\*\*) If the cylinder temperatures are higher than the recommended maximum temperatures, the max. residence time in the barrel has to be reduced.

Processing Notes

### Pre-Drying

CELANEX should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be  $\leq -30^{\circ}\text{C}$ . The time between drying and processing should be as short as possible.

### Storage

For subsequent storage of the material in the dryer until processed ( $\leq 60$  h) it is necessary to lower the temperature to 100° C.