

# CELANEX® 3202-2

## CELANEX® PBT

Celanex 3202-2 is a 20% glass-filled Polybutylene Terephthalate that has an excellent balance of mechanical properties and processability. It contains an internal lubricant for mold release.

### Product information

Resin Identification	PBT-GF20	ISO 1043
Part Marking Code	>PBT-GF20<	ISO 11469

### Rheological properties

Melt mass-flow rate	22 g/10min	ISO 1133
Melt mass-flow rate, Temperature	250 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage range, parallel	0.4 - 0.8 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile stress at break, 5mm/min	115 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.2 %	ISO 527-1/-2
Flexural modulus	6800 MPa	ISO 178
Flexural strength	180 MPa	ISO 178
Izod notched impact strength, 23°C	7 kJ/m <sup>2</sup>	ISO 180/1A

### Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
-------------------------------	--------	----------------

### Physical/Other properties

Humidity absorption, 2mm	0.1 %	Sim. to ISO 62
Density	1450 kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Screw tangential speed	0.1 - 0.3 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	130 °C

### Characteristics

Processing	Injection Moulding
Additives	Release agent

# CELANEX® 3202-2

CELANEX® PBT

## Additional information

Injection molding

### Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints  $<-30^{\circ}\text{F}$  ( $-34^{\circ}\text{C}$ ) at  $250^{\circ}\text{F}$  ( $121^{\circ}\text{C}$ ) for 4 hours.

### Processing

Rear Temperature 450-470(230-240) deg F (deg C)  
Center Temperature 460-480(235-250) deg F (deg C)  
Front Temperature 470-500(240-260) deg F (deg C)  
Nozzle Temperature 480-500(250-260) deg F (deg C)  
Melt Temperature 460-500(235-260) deg F (deg C)  
Mold Temperature 150-200(65-93) deg F (deg C)  
Back Pressure 0-50 psi  
Screw Speed Medium  
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Notes

### Pre-Drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints  $<-40^{\circ}\text{F}$  ( $-40^{\circ}\text{C}$ ) at  $250^{\circ}\text{F}$  ( $121^{\circ}\text{C}$ ) for 4 hours.

### Storage

For subsequent storage of the material in the dryer until processed ( $\leq 60$  h) it is necessary to lower the temperature to  $100^{\circ}\text{C}$ .