

## CELANEX® 3300C - PBT

### Description

Celanex 3300C is a general purpose, 30% glass reinforced, polybutylene terephthalate.

Physical properties	Value	Unit	Test Standard
Density	1530	kg/m <sup>3</sup>	ISO 1183

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	9600	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	165	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	2.5	%	ISO 527-2/1A
Flexural modulus, 23°C	7800	MPa	ISO 178
Flexural strength, 23°C	195	MPa	ISO 178
Charpy impact strength, 23°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod impact unnotched, 23°C	40	kJ/m <sup>2</sup>	ISO 180/1U

Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
DTUL at 1.8 MPa	205	°C	ISO 75-1, -2
DTUL at 0.45 MPa	215	°C	ISO 75-1, -2
Flammability at thickness h	HB	class	UL 94
thickness tested (h)	0.80	mm	UL 94

Electrical properties	Value	Unit	Test Standard
Volume resistivity	>1E16	Ohm*m	IEC 60093
Surface resistivity	>1E14	Ohm	IEC 60093
Electric strength	21	kV/mm	IEC 60243-1
Comparative tracking index	425	-	IEC 60112

### Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Necessary low maximum residual moisture content	0.02	%	-
Drying time	4	h	-
Drying temperature	120 - 130	°C	-

Temperature	Value	Unit	Test Standard
Hopper temperature	20 - 50	°C	-
Feeding zone temperature	20 - 50	°C	-
Zone1 temperature	230 - 240	°C	-
Zone2 temperature	235 - 250	°C	-
Zone3 temperature	235 - 250	°C	-
Zone4 temperature	240 - 260	°C	-
Nozzle temperature	250 - 260	°C	-
Melt temperature	225	°C	-
Mold temperature	65 - 93	°C	-
Hot runner temperature	250 - 260	°C	-

Speed	Value	Unit	Test Standard
Injection speed	medium-fast	-	-

### Other text information

#### Pre-drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should

---

## CELANEX® 3300C - PBT

---

be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.

### Longer pre-drying times/storage

---

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

### Injection molding

---

Rear Temperature 450-470(230-240) deg F (deg C)  
Center Temperature 460-480(235-250) deg F (deg C)  
Front Temperature 470-500(240-260) deg F (deg C)  
Nozzle Temperature 480-500(250-260) deg F (deg C)  
Melt Temperature 460-500(235-260) deg F (deg C)  
Mold Temperature 150-200(65-93) deg F (deg C)  
Back Pressure 0-50 psi  
Screw Speed Medium  
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

### Characteristics

---

#### Product Categories

Glass reinforced

#### Delivery Form

Pellets

#### Processing

Injection molding

#### Additives

Lubricants