

# CELANEX® 4022

## CELANEX® PBT

Celanex 4022 is a white PBT resin typically used for applications requiring very opaque parts.

### Product information

Resin Identification	PBT-MD16	ISO 1043
Part Marking Code	>PBT-MD16<	ISO 11469

### Rheological properties

Melt mass-flow rate	19 g/10min	ISO 1133
Melt mass-flow rate, Temperature	250 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage range, parallel	1.8 - 2 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	3200 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	58 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	8 %	ISO 527-1/-2
Flexural strength	86 MPa	ISO 178
Charpy impact strength, 23°C	33 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	3.5 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.37 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10°C/min	223 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	63 °C	ISO 75-1/-2

### Flammability

Thickness tested	0.79 mm	IEC 60695-11-10
------------------	---------	-----------------

### Electrical properties

Comparative tracking index	400	IEC 60112
----------------------------	-----	-----------

### Physical/Other properties

Density	1460 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Screw tangential speed	0.1 - 0.3 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C

# CELANEX® 4022

## CELANEX® PBT

Max. mould temperature 130 °C

### Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent, Mineral Filler
Special characteristics	Specialty appearance

### Additional information

Injection molding

### Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30 °F (-34 °C) at 250 °F (121 °C) for 4 hours.

### Processing

Rear Temperature 450-470(230-240) deg F (deg C)  
 Center Temperature 460-480(235-250) deg F (deg C)  
 Front Temperature 470-500(240-260) deg F (deg C)  
 Nozzle Temperature 480-500(250-260) deg F (deg C)  
 Melt Temperature 460-500(235-260) deg F (deg C)  
 Mold Temperature 150-200(65-93) deg F (deg C)  
 Back Pressure 0-50 psi  
 Screw Speed Medium  
 Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

### Automotive

OEM	STANDARD
Continental	SN 57908-4