

CELANEX® 6402 ECO-R

CELANEX® PBT

Celanex 6402® ECO-R is a 40% Glass/ mineral filled polyester with 25% Post Consumer Recycled content. It is available in natural, black and various colors including metallic colors.

Product information

Resin Identification	(PBT+PET)-(GF+MD)40	ISO 1043
Part Marking Code	>(PBT+PET)-(GF+MD)40<	ISO 11469

Rheological properties

Melt mass-flow rate	22 g/10min	ISO 1133
Melt mass-flow rate, Temperature	265 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage range, parallel	0.1 - 0.2 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.4 - 0.6 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	13500 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	147 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.1 %	ISO 527-1/-2
Flexural modulus	12500 MPa	ISO 178
Flexural strength	220 MPa	ISO 178
Charpy notched impact strength, 23°C	7.5 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	6.9 kJ/m ²	ISO 180/1A
Izod impact strength, 23°C	64.1 kJ/m ²	ISO 180/1U
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	205 °C	ISO 75-1/-2
---	--------	-------------

Physical/Other properties

Density	1660 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	265 °C
Min. melt temperature	255 °C
Max. melt temperature	275 °C
Screw tangential speed	0.1 - 0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	90 °C
Max. mould temperature	130 °C
Back pressure	0.34 MPa
Ejection temperature	174 °C

CELANEX® 6402 ECO-R

CELANEX® PBT

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent
Special characteristics	High Gloss, Low Warpage
Sustainability	Recycled Content

Additional information

Injection molding

Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30 °F (-34 °C) at 250 °F (121 °C) for minimum 4 hours.

Processing

Rear Temperature 450-480 (230-250) deg F (deg C)
 Center Temperature 460-490(235-255) deg F (deg C)
 Front Temperature 470-500 (240-260) deg F (deg C)
 Nozzle Temperature 480-510 (250-265) deg F (deg C)
 Melt Temperature 460-510 (235-265) deg F (deg C)
 Mold Temperature 150-200(65-93) deg F (deg C)
 Back Pressure 0-50 psi
 Screw Speed Medium
 Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Notes

Pre-Drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40 °F (-40 °C) at 250 °F (121 °C) for 4 hours.

Storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

CELANEX® 6402 ECO-R

CELANEX® PBT

Automotive

OEM

Ford

Stellantis - Chrysler

Stellantis - Chrysler

STANDARD

WRS-M4D625-A3

MS.50103 / CPN-5372

MS.50103 / CPN-5372R

ADDITIONAL INFORMATION

Natural, Black, Standard colors

100% Color Match

100% Color Match