

Crastin® FR685NH1 BK591LM

THERMOPLASTIC POLYESTER RESIN

Crastin® FR685NH1 BK591LM is a 30% Glass Reinforced, Flame Retardant, Non-Halogenated, Polybutylene Terephthalate

Product information

Resin Identification	PBT-GF30 FR(40+30)	ISO 1043
Part Marking Code	>PBT-GF30 FR(40+30)<	ISO 11469

Rheological properties

Melt volume-flow rate	26 cm ³ /10min	ISO 1133
Temperature	250 °C	
Load	5 kg	
Viscosity number	88 cm ³ /g	ISO 307, 1628

Typical mechanical properties

Tensile modulus	10800 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	96 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.1 %	ISO 527-1/-2
Charpy notched impact strength, 23°C	6.9 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34	

Thermal properties

Melting temperature, 10°C/min	224 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	55 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	208 °C	ISO 75-1/-2
Thermal conductivity, flow	0.37 W/(m K)	ISO 22007-2
RTI, electrical, 0.75mm	130 ^[1] °C	UL 746B
RTI, electrical, 1.5mm	130 ^[1] °C	UL 746B
RTI, electrical, 3.0mm	130 ^[1] °C	UL 746B
RTI, impact, 0.75mm	125 ^[1] °C	UL 746B
RTI, impact, 1.5mm	125 ^[1] °C	UL 746B
RTI, impact, 3.0mm	125 ^[1] °C	UL 746B
RTI, strength, 0.75mm	140 ^[1] °C	UL 746B
RTI, strength, 1.5mm	140 ^[1] °C	UL 746B
RTI, strength, 3.0mm	140 ^[1] °C	UL 746B

[1]: <https://iq.ul.com/ul/cert.aspx?ULID=104511959>

Flammability

Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
Thickness tested	0.4 mm	IEC 60695-11-10
UL recognition	yes ^[1]	UL 94
Glow Wire Flammability Index, 0.4mm	960 ^[1] °C	IEC 60695-2-12
Glow Wire Flammability Index, 0.75mm	960 ^[1] °C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960 ^[1] °C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960 ^[1] °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	750 ^[1] °C	IEC 60695-2-13
Glow Wire Ignition Temperature, 0.4mm	750 ^[1] °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 1.5mm	750 ^[1] °C	IEC 60695-2-13

Crastin® FR685NH1 BK591LM

THERMOPLASTIC POLYESTER RESIN

Glow Wire Ignition Temperature, 3.0mm	800 ^[1] °C	IEC 60695-2-13
FMVSS Class	SE	ISO 3795 (FMVSS 302)
[1]: https://q.ul.com/ul/cert.aspx?ULID=104511959		

Electrical properties

Relative permittivity, 1000Hz	4.07 ^[OT]	IEC 62631-2-1
Dissipation factor, 100Hz	35 ^[OT] E-4	IEC 62631-2-1
Volume resistivity	>1E13 Ohm.m	IEC 62631-3-1
Electric strength	36 kV/mm	IEC 60243-1
Comparative tracking index	600	IEC 60112
[OT]: One time tested		

Physical/Other properties

Humidity absorption, 2mm	0.1 ^[DS] %	Sim. to ISO 62
Water absorption, 2mm	0.25 ^[DS] %	Sim. to ISO 62
Density	1570 kg/m ³	ISO 1183
[DS]: Derived from similar grade		

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	130 °C
Hold pressure range	≥60 MPa
Hold pressure time	3 s/mm
Back pressure	As low as possible
Ejection temperature	170 °C

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent, Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant