

Crastin® SK642FR BK851

THERMOPLASTIC POLYESTER RESIN

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.

If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® SK642FR is a 15% glass fibre reinforced, flame retardant polybutylene terephthalate for injection moulding. It has a UL94 V-0 rating @ 1.5mm.

Product information

Resin Identification	PBT- GF15FR(17)	ISO 1043
Part Marking Code	>PBT-GF15FR(17)<	ISO 11469

Rheological properties

Viscosity number	110 cm ³ /g	ISO 307, 1157, 1628
Moulding shrinkage, parallel	0.7 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.2 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	7200 MPa	ISO 527-1/-2
Stress at break, 5mm/min	100 MPa	ISO 527-1/-2
Strain at break, 5mm/min	3.4 %	ISO 527-1/-2
Flexural Strength	155 MPa	ISO 178
Charpy impact strength, 23°C	53 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	7.4 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.35	

Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	55 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	203 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	218 °C	ISO 75-1/-2
RTI, electrical, 0.75mm	140 °C	UL 746B
RTI, electrical, 1.5mm	140 °C	UL 746B
RTI, electrical, 3mm	140 °C	UL 746B
RTI, electrical, 6mm	140 °C	UL 746B

Crastin® SK642FR BK851

THERMOPLASTIC POLYESTER RESIN

RTI, impact, 0.75mm	130 °C	UL 746B
RTI, impact, 1.5mm	130 °C	UL 746B
RTI, impact, 3mm	130 °C	UL 746B
RTI, impact, 6mm	130 °C	UL 746B
RTI, strength, 0.75mm	140 °C	UL 746B
RTI, strength, 1.5mm	140 °C	UL 746B
RTI, strength, 3mm	140 °C	UL 746B
RTI, strength, 6mm	140 °C	UL 746B

Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	UL 94
Thickness tested	1.5 mm	UL 94
UL recognition	yes	UL 94
Burning Behav. at thickness h	V-0 class	UL 94
Thickness tested	0.75 mm	UL 94
UL recognition	yes	UL 94
Burning Behav. 5V at thickness h	5VA class	UL 94
Thickness tested	1.5 mm	UL 94
UL recognition	yes	UL 94
Oxygen index	32 %	ISO 4589-1/-2
Glow Wire Flammability Index, 3mm	960 °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 3mm	775 °C	IEC 60695-2-13
FMVSS Class	DNI	ISO 3795 (FMVSS 302)

Electrical properties

Relative permittivity, 100Hz	4.2	IEC 62631-2-1
Relative permittivity, 1MHz	3.9	IEC 62631-2-1
Dissipation factor, 100Hz	19.6 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	171 E-4	IEC 62631-2-1
Volume resistivity	>1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	1E14 Ohm	IEC 62631-3-2
Electric strength	32 kV/mm	IEC 60243-1
Comparative tracking index	200	IEC 60112

Other properties

Density	1580 kg/m ³	ISO 1183
---------	------------------------	----------


Injection

Drying Recommended	yes	
Drying Temperature	120 °C	
Drying Time, Dehumidified Dryer	2 - 4 h	
Processing Moisture Content	≤0.04 %	
Melt Temperature Optimum	250 °C	Internal
Min. melt temperature	240 °C	

Crastin® SK642FR BK851

THERMOPLASTIC POLYESTER RESIN


Stress-strain
(measured on Crastin® SK642FR NC010)



Crastin® SK642FR BK851

THERMOPLASTIC POLYESTER RESIN

Secant modulus-strain
(measured on Crastin® SK642FR NC010)



Crastin® SK642FR BK851

THERMOPLASTIC POLYESTER RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✗ ISO 1817 Liquid 1 - E5, 60°C
 - ✗ ISO 1817 Liquid 2 - M15E4, 60°C
 - ✗ ISO 1817 Liquid 3 - M3E7, 60°C
 - ✗ ISO 1817 Liquid 4 - M15, 60°C
 - ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
 - ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
 - ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
 - ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
 - ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C
-

Crastin® SK642FR BK851

THERMOPLASTIC POLYESTER RESIN

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✓ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✓ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✗ DOT No. 4 Brake fluid, 130°C
- ✗ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✗ Water, 90°C
- ✓ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
 - ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).
-