

CELSTRAN® PCABS-SF6-05 AF3005 NATURAL

CELSTRAN® Long Fibre

Celstran® PCABS-SF6-05 AF3005 NATURAL is composed of a polycarbonate/ABS polymer matrix with 6 wt% stainless steel fiber. Celstran® long stainless steel fiber filled PC/ABS materials provide electrical conductivity needed to reach desired levels of electrostatic dissipation (ESD) and electromagnetic interference (EMI)/radio frequency interference (RFI) shielding. These materials have significant advantages over short stainless steel fiber filled plastics. Conductivity properties increase by nearly 100 times when comparing to similar loadings. Celstran®PCABS-SF-05 materials contain continuous stainless steel filaments wetted and encapsulated by PC/ABS resin. Various stainless steel loadings can be selected to meet specific end use requirements.

Product information

Resin Identification	(PC+ABS)-LMEF(x)6	ISO 1043
Part Marking Code	>(PC+ABS)-LMEF(x)6<	ISO 11469

Typical mechanical properties

Tensile modulus	2800 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	60 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.8 %	ISO 527-1/-2
Flexural modulus	2800 MPa	ISO 178
Flexural strength	60 MPa	ISO 178
Izod notched impact strength, 23°C	70 kJ/m ²	ISO 180/1A
Poisson's ratio	0.37 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	110 °C	ISO 75-1/-2
RTI, electrical, 1.5mm	60 °C	UL 746B
RTI, impact, 1.5mm	60 °C	UL 746B
RTI, strength, 1.5mm	60 °C	UL 746B

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
UL recognition	yes	UL 94

Physical/Other properties

Density	1200 kg/m ³	ISO 1183
---------	------------------------	----------

Characteristics

Processing	Injection Moulding
Special characteristics	Increased electrical conductivity, Static dissipative