

Rynite® 940 BK505

THERMOPLASTIC POLYESTER RESIN

Common features of Rynite® thermoplastic polyester include mechanical and physical properties such as excellent balance of strength and stiffness, dimensional stability, creep resistance, heat resistance, high surface gloss and good inherent electrical properties at elevated temperature. It can be processed over a broad temperature range and has excellent flow properties.

Rynite® thermoplastic polyester resins are typically used in demanding applications in the automotive, electrical and electronics, appliances where they successfully replace metals and thermosets, as well as other thermoplastic polymers.

Rynite® 940 BK505 is a 40% mica/glass reinforced modified polyethylene terephthalate resin with low warpage, high stiffness and strength, and excellent electrical properties.

Product information

Resin Identification	PET-(GF+MD)4 0	ISO 1043
Part Marking Code	>PET-(GF+MD)40<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.2 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	12500 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	110 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.8 %	ISO 527-1/-2
Flexural modulus	13000 MPa	ISO 178
Charpy impact strength, 23°C	35 kJ/m ²	ISO 179/1eU
Charpy impact strength, -40°C	35 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	7 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	6 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33	

Thermal properties

Melting temperature, 10°C/min	250 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	220 °C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	241 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel, -40-23°C	22 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	15 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel, 55-160°C	6 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, -40-23°C	54 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	60 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, 55-160°C	84 E-6/K	ISO 11359-1/-2
RTI, electrical, 0.75mm	75 °C	UL 746B
RTI, impact, 0.75mm	75 °C	UL 746B
RTI, strength, 0.75mm	75 °C	UL 746B

Rynite® 940 BK505

THERMOPLASTIC POLYESTER RESIN

Flammability

Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	0.75 mm	IEC 60695-11-10
UL recognition	yes	UL 94
Glow Wire Flammability Index, 3.0mm	925 °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 3.0mm	900 °C	IEC 60695-2-13
FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80 mm/min	ISO 3795 (FMVSS 302)

Electrical properties

Relative permittivity, 100Hz	4.2	IEC 62631-2-1
Relative permittivity, 1MHz	3.9	IEC 62631-2-1
Dissipation factor, 100Hz	70 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	146 E-4	IEC 62631-2-1
Volume resistivity	1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	1E14 Ohm	IEC 62631-3-2
Electric strength	33 kV/mm	IEC 60243-1
Comparative tracking index	250	IEC 60112

Physical/Other properties

Density	1640 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.02 ^[1] %
Melt Temperature Optimum	290 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	110 °C
Min. mould temperature	95 °C
Max. mould temperature	125 ^[2] °C
Hold pressure range	≥80 MPa
Hold pressure time	4 s/mm
Back pressure	As low as possible MPa
Ejection temperature	202 °C

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent

Rynite® 940 BK505

THERMOPLASTIC POLYESTER RESIN

Special characteristics

Low Warpage

Automotive

OEM

Stellantis - Chrysler

STANDARD

MS.50103 / CPN-3080

ADDITIONAL INFORMATION

Black