

Rynite® FR533NH BK507 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Common features of Rynite® thermoplastic polyester include mechanical and physical properties such as excellent balance of strength and stiffness, dimensional stability, creep resistance, heat resistance, high surface gloss and good inherent electrical properties at elevated temperature. It can be processed over a broad temperature range and has excellent flow properties.

Rynite® thermoplastic polyester resins are typically used in demanding applications in the automotive, electrical and electronics, appliances where they successfully replace metals and thermosets, as well as other thermoplastic polymers.

Rynite® FR533NH BK507 is a 33% glass reinforced, modified polyethylene terephthalate resin using a non-halogenated flame retardant.

Product information

| | | |
|----------------------|--------------------|-----------|
| Resin Identification | PET- GF33FR(40) | ISO 1043 |
| Part Marking Code | >PET-GF33FR(40)< | ISO 11469 |

Rheological properties

| | | |
|------------------------------|-------|-----------------|
| Moulding shrinkage, parallel | 0.4 % | ISO 294-4, 2577 |
| Moulding shrinkage, normal | 0.7 % | ISO 294-4, 2577 |

Typical mechanical properties

| | | |
|---------------------------------------|---------------------|--------------|
| Tensile modulus | 12900 MPa | ISO 527-1/-2 |
| Tensile stress at break, 5mm/min | 82 MPa | ISO 527-1/-2 |
| Tensile strain at break, 5mm/min | 0.9 % | ISO 527-1/-2 |
| Flexural modulus | 13100 MPa | ISO 178 |
| Flexural strength | 140 MPa | ISO 178 |
| Charpy notched impact strength, 23°C | 9 kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -40°C | 9 kJ/m ² | ISO 179/1eA |
| Poisson's ratio | 0.33 | |

Thermal properties

| | | |
|--|----------|----------------|
| Melting temperature, 10°C/min | 249 °C | ISO 11357-1/-3 |
| Glass transition temperature, 10°C/min | 90 °C | ISO 11357-1/-3 |
| Temperature of deflection under load, 1.8 MPa | 240 °C | ISO 75-1/-2 |
| Coeff. of linear therm. expansion, parallel, -40-23°C | 16 E-6/K | ISO 11359-1/-2 |
| Coefficient of linear thermal expansion (CLTE), parallel | 18 E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, parallel, 55-160°C | 12 E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, normal, -40-23°C | 54 E-6/K | ISO 11359-1/-2 |
| Coefficient of linear thermal expansion (CLTE), normal | 78 E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, normal, 55-160°C | 93 E-6/K | ISO 11359-1/-2 |
| RTI, electrical, 0.4mm | 155 °C | UL 746B |
| RTI, electrical, 0.75mm | 155 °C | UL 746B |
| RTI, electrical, 1.5mm | 155 °C | UL 746B |
| RTI, electrical, 3.0mm | 155 °C | UL 746B |
| RTI, impact, 0.75mm | 160 °C | UL 746B |
| RTI, impact, 1.5mm | 170 °C | UL 746B |

Rynite® FR533NH BK507 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

| | | |
|-----------------------|--------|---------|
| RTI, impact, 3.0mm | 170 °C | UL 746B |
| RTI, strength, 0.75mm | 160 °C | UL 746B |
| RTI, strength, 1.5mm | 170 °C | UL 746B |
| RTI, strength, 3.0mm | 170 °C | UL 746B |

Flammability

| | | |
|--------------------------------------|-----------|-----------------|
| Burning Behav. at 1.5mm nom. thickn. | V-0 class | IEC 60695-11-10 |
| Thickness tested | 1.5 mm | IEC 60695-11-10 |
| UL recognition | yes | UL 94 |
| Burning Behav. at thickness h | V-0 class | IEC 60695-11-10 |
| Thickness tested | 0.4 mm | IEC 60695-11-10 |
| UL recognition | yes | UL 94 |
| Railway classification | R22 | EN 45545-2 |
| Railway classification rating | HL1 | EN 45545-2 |

Electrical properties

| | | |
|--------------------|------------|---------------|
| Volume resistivity | 1E13 Ohm.m | IEC 62631-3-1 |
| Electric strength | 31 kV/mm | IEC 60243-1 |

Physical/Other properties

| | | |
|---------|------------------------|----------|
| Density | 1600 kg/m ³ | ISO 1183 |
|---------|------------------------|----------|

Injection

| | |
|---------------------------------|------------------------|
| Drying Recommended | yes |
| Drying Temperature | 120 °C |
| Drying Time, Dehumidified Dryer | 4 - 6 h |
| Processing Moisture Content | ≤0.01 ^[1] % |
| Melt Temperature Optimum | 280 °C |
| Min. melt temperature | 270 °C |
| Max. melt temperature | 280 °C |
| Min. mould temperature | 120 °C |
| Max. mould temperature | 140 ^[2] °C |

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)

Characteristics

| | |
|-------------------------|---|
| Processing | Injection Moulding |
| Delivery form | Pellets |
| Additives | Flame retardant, Non-halogenated/Red phosphorous free flame retardant |
| Special characteristics | Flame retardant, Heat stabilised or stable to heat |

Rynite® FR533NH BK507 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Automotive

OEM
Stellantis

STANDARD
B62 0300 / 61/223E-219M/C4

ADDITIONAL INFORMATION
01378_19_02644