

Grilamid L 25 W 40 NZ

PA12-I

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA12-P, EHL, 22-002

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	300 / 250	MPa	ISO 527-1/-2
Yield stress	- / 20	MPa	ISO 527-1/-2
Yield strain	- / 45	%	ISO 527-1/-2
Nominal strain at break	- / >50	%	ISO 527-1/-2
Stress at break	45 / 30	MPa	ISO 527-1/-2
Strain at break	>50 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	12 / 13	kJ/m ²	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	- / 25	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	173 / -	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	40 / -	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	50 / -	°C	ISO 75-1/-2
Max. usage temperature (long term)	80	°C	ISO 2578
Max. usage temperature (short term)	110	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	- / 1E11	Ohm*m	IEC 60093
Surface resistivity	- / 1E12	Ohm	IEC 60093
Electric strength	- / 32	kV/mm	IEC 60243-1
Comparative tracking index	- / 600	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	1.4 / -	%	Sim. to ISO 62
Humidity absorption	0.7 / -	%	Sim. to ISO 62
Density	1000 / -	kg/m ³	ISO 1183

Characteristics

Processing

Other Extrusion

Delivery form

Granules

Additives

Plasticizer

Special Characteristics

High impact or impact modified, Improved UV resistance (outdoor use), Improved heat resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Product Attributes

Flexible, High viscosity

Automotive

Compressed air systems, Fuel systems

Grilamid L 25 W 40 NZ
PA12-I

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Industry & Consumer goods

Hydraulics & Pneumatics
