

**Grilamid LVX-65H SST black 9288**

PA12-GF65

EMS-GRIVORY | a unit of EMS-CHEMIE AG

**Product Texts**

Product designation according to ISO 1874:

PA12, MHR, 18-190, GF65

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	<b>19000 / 17000</b>	MPa	ISO 527-1/-2
Stress at break	<b>200 / 185</b>	MPa	ISO 527-1/-2
Strain at break	<b>2.5 / 2.5</b>	%	ISO 527-1/-2
Charpy impact strength (+23°C)	<b>85 / 85</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	<b>80 / 80</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	<b>20 / 20</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	<b>20 / 20</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	<b>210 / 190</b>	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	<b>178 / -</b>	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	<b>175 / -</b>	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	<b>160 / -</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	<b>10 / -</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	<b>70 / -</b>	E-6/K	ISO 11359-1/-2
Max. usage temperature (long term)	<b>90 - 120</b>	°C	ISO 2578
Max. usage temperature (short term)	<b>150</b>	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	<b>- / 1E11</b>	Ohm*m	IEC 60093
Surface resistivity	<b>- / 1E12</b>	Ohm	IEC 60093
Electric strength	<b>35 / 35</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>- / 600</b>	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	<b>0.8 / -</b>	%	Sim. to ISO 62
Humidity absorption	<b>0.4 / -</b>	%	Sim. to ISO 62
Density	<b>1700 / -</b>	kg/m <sup>3</sup>	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	<b>0.1 / -</b>	%	ISO 294-4, 2577
Molding shrinkage (normal)	<b>0.3 / -</b>	%	ISO 294-4, 2577

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Granules

**Special Characteristics**

High impact or impact modified, Improved UV resistance (outdoor use), Improved heat resistance

**Product Attributes**

Improved flowability and demoulding

**Automotive**

Compressed air systems, Hydraulic systems, Automotive electr. and electronics, lighting, Powertrain and Chassis

**Electricals & Electronics**

Electrical appliances, Electrical equipment, Connectors, Mobile

Grilamid LVX-65H SST black 9288

PA12-GF65

EMS-GRIVORY | a unit of EMS-CHEMIE AG

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa

phones and other portable devices

#### Industry & Consumer goods

Housewares, Hydraulics & Pneumatics, Mechanical Engineering,  
Medical devices, Power transmission, Sanitary, water and gas  
supply, Sports & Leisure, Tools & Accessories

---