

Grilamid TR 55 LX

PA12/MACMI

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA 12/MACMI + PA 12, GHLT, 14-020

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	2000 / 1900	MPa	ISO 527-1/-2
Yield stress	75 / 70	MPa	ISO 527-1/-2
Yield strain	7 / 6	%	ISO 527-1/-2
Nominal strain at break	>50 / >50	%	ISO 527-1/-2
Stress at break	- / 40	MPa	ISO 527-1/-2
Charpy impact strength (+23°C)	- / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	- / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	- / 9	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	- / 8	kJ/m ²	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	- / 110	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Glass transition temperature (10°C/min)	110 / -	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	80 / -	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	90 / -	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	90 / -	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	90 / -	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	IEC 60695-11-10
Max. usage temperature (long term)	80	°C	ISO 2578
Max. usage temperature (short term)	95	°C	EMS


Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	- / 1E11	Ohm*m	IEC 60093
Surface resistivity	- / 1E12	Ohm	IEC 60093
Electric strength	- / 32	kV/mm	IEC 60243-1
Comparative tracking index	- / 600	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	2.5 / -	%	Sim. to ISO 62
Humidity absorption	1 / -	%	Sim. to ISO 62
Density	1040 / -	kg/m ³	ISO 1183


Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	0.5 / -	%	ISO 294-4, 2577
Molding shrinkage (normal)	0.6 / -	%	ISO 294-4, 2577

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Dynamic Shear modulus-temperature




Stress-strain




Grilamid TR 55 LX
PA12/MACMI

EMS-GRIVORY | a unit of EMS-CHEMIE AG


Secant modulus-strain




Stress-strain (isochronous) 23°C



Creep curve °C



Creep modulus-time 23°C



Characteristics

Processing

Injection Molding

Delivery form

Granules

Special Characteristics

Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Electricals & Electronics

Electrical appliances, Electrical equipment, Cables & Tubes, Energy distribution, Lighting, Mobile phones and other portable devices

Industry & Consumer goods

Housewares, Hydraulics & Pneumatics, Mechanical Engineering, Medical devices, Power transmission, Sanitary, water and gas supply, Sports & Leisure, Tools & Accessories

Optics

Optical components, Sunglasses, Spectacle frames

Grilamid TR 55 LX
PA12/MACMI

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Attributes

Improved alcohol resistance

Burning Behaviour

UL V2

Automotive

Automotive electr. and electronics, lighting, Cooling and climate control, Fuel systems, Powertrain and Chassis , Interior

Biocompatibility









ISO 10993

Potable Water Contact




NSF 61

Chemical Media Resistance




Acids

-  Acetic Acid (5% by mass) (23°C)
-  Citric Acid solution (10% by mass) (23°C)
-  Lactic Acid (10% by mass) (23°C)
-  Hydrochloric Acid (36% by mass) (23°C)
-  Nitric Acid (40% by mass) (23°C)
-  Sulfuric Acid (38% by mass) (23°C)
-  Sulfuric Acid (5% by mass) (23°C)
-  Chromic Acid solution (40% by mass) (23°C)




Bases

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)


Hydrocarbons

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)





Ketones

-  Acetone (23°C)

Ethers

-  Diethyl ether (23°C)

Mineral oils










-  SAE 10W40 multigrade motor oil (23°C)
-  SAE 10W40 multigrade motor oil (130°C)
-  SAE 80/90 hypoid-gear oil (130°C)
-  Insulating Oil (23°C)

Standard Fuels






Grilamid TR 55 LX

PA12/MACMI










EMS-GRIVORY | a unit of EMS-CHEMIE AG

-  ISO 1817 Liquid 1 (60°C)
-  ISO 1817 Liquid 2 (60°C)
-  ISO 1817 Liquid 3 (60°C)
-  ISO 1817 Liquid 4 (60°C)
-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

Salt solutions

-  Sodium Chloride solution (10% by mass) (23°C)
-  Sodium Hypochlorite solution (10% by mass) (23°C)
-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)
-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethyl Acetate (23°C)
-  Hydrogen peroxide (23°C)
-  DOT No. 4 Brake fluid (130°C)
-  Ethylene Glycol (50% by mass) in water (108°C)
-  1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)
-  Phenol solution (5% by mass) (23°C)