

Grilon BG-30

PA6-GF30

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA6, MHR, 14-100N, GF30

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	10000 / 6500	MPa	ISO 527-1/-2
Stress at break	190 / 110	MPa	ISO 527-1/-2
Strain at break	3.5 / 6.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	85 / 95	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	70 / 70	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 20	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	9 / 9	kJ/m ²	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	210 / 100	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	222 / -	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / -	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	135 / -	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	30 / -	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	110 / -	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	IEC 60695-11-10
Max. usage temperature (long term)	90 - 110	°C	ISO 2578
Max. usage temperature (short term)	160	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	1E12 / 1E10	Ohm*m	IEC 60093
Surface resistivity	- / 1E12	Ohm	IEC 60093
Electric strength	34 / 31	kV/mm	IEC 60243-1
Comparative tracking index	- / 550	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	7 / -	%	Sim. to ISO 62
Humidity absorption	2 / -	%	Sim. to ISO 62
Density	1350 / -	kg/m ³	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	0.1 / -	%	ISO 294-4, 2577
Molding shrinkage (normal)	0.6 / -	%	ISO 294-4, 2577


Diagrams

Grilon BG-30


PA6-GF30

EMS-GRIVORY | a unit of EMS-CHEMIE AG


Dynamic Shear modulus-temperature



Dynamic Shear modulus-temperature



Tensile modulus-temperature



Characteristics

Processing

Injection Molding

Automotive

Air intake systems, Interior

Delivery form

Granules

Electricals & Electronics

Electrical appliances, Electrical equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Chemical Media Resistance






Acids

- 😊 Acetic Acid (5% by mass) (23°C)
- 😊 Citric Acid solution (10% by mass) (23°C)
- 😊 Lactic Acid (10% by mass) (23°C)




Grilon BG-30

PA6-GF30




EMS-GRIVORY | a unit of EMS-CHEMIE AG

-  Hydrochloric Acid (36% by mass) (23°C)
-  Nitric Acid (40% by mass) (23°C)
-  Sulfuric Acid (38% by mass) (23°C)
-  Sulfuric Acid (5% by mass) (23°C)
-  Chromic Acid solution (40% by mass) (23°C)




Bases

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)


Hydrocarbons

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)





Ketones

-  Acetone (23°C)










Ethers

-  Diethyl ether (23°C)





Mineral oils

-  SAE 10W40 multigrade motor oil (23°C)
-  SAE 10W40 multigrade motor oil (130°C)
-  SAE 80/90 hypoid-gear oil (130°C)
-  Insulating Oil (23°C)

Standard Fuels

-  ISO 1817 Liquid 1 (60°C)
-  ISO 1817 Liquid 2 (60°C)
-  ISO 1817 Liquid 3 (60°C)
-  ISO 1817 Liquid 4 (60°C)
-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)


Salt solutions

-  Sodium Chloride solution (10% by mass) (23°C)
-  Sodium Hypochlorite solution (10% by mass) (23°C)
-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)










Grilon BG-30

PA6-GF30

EMS-GRIVORY | a unit of EMS-CHEMIE AG

 Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethyl Acetate (23°C)
 -  Hydrogen peroxide (23°C)
 -  DOT No. 4 Brake fluid (130°C)
 -  Ethylene Glycol (50% by mass) in water (108°C)
 -  1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
 -  50% Oleic acid + 50% Olive Oil (23°C)
 -  Water (23°C)
 -  Deionized water (90°C)
 -  Phenol solution (5% by mass) (23°C)
-