

**Grilon BG-50 S**

PA6-GF50

EMS-GRIVORY | a unit of EMS-CHEMIE AG

**Product Texts**

Product designation according to ISO 1874:

PA 6, MH, 14-190, GF50

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	<b>17500 / 11500</b>	MPa	ISO 527-1/-2
Stress at break	<b>245 / 165</b>	MPa	ISO 527-1/-2
Strain at break	<b>3 / 6</b>	%	ISO 527-1/-2
Charpy impact strength (+23°C)	<b>90 / 95</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	<b>85 / 90</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	<b>15 / 25</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	<b>11 / 12</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	<b>270 / 155</b>	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	<b>222 / -</b>	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	<b>210 / -</b>	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	<b>170 / -</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	<b>15 / -</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	<b>100 / -</b>	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	<b>HB / -</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / -</b>	mm	IEC 60695-11-10
Max. usage temperature (long term)	<b>90 - 140</b>	°C	ISO 2578
Max. usage temperature (short term)	<b>160</b>	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	<b>1E12 / 1E12</b>	Ohm*m	IEC 60093
Surface resistivity	<b>- / 1E12</b>	Ohm	IEC 60093
Electric strength	<b>40 / 37</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>- / 575</b>	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	<b>5 / -</b>	%	Sim. to ISO 62
Humidity absorption	<b>1.5 / -</b>	%	Sim. to ISO 62
Density	<b>1580 / -</b>	kg/m <sup>3</sup>	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	<b>0.1 / -</b>	%	ISO 294-4, 2577
Molding shrinkage (normal)	<b>0.5 / -</b>	%	ISO 294-4, 2577


**Diagrams**

Grilon BG-50 S


PA6-GF50

EMS-GRIVORY | a unit of EMS-CHEMIE AG


Viscosity-shear rate




Shearstress-shear rate



Dynamic Shear modulus-temperature



Dynamic Shear modulus-temperature




Grilon BG-50 S


PA6-GF50

EMS-GRIVORY | a unit of EMS-CHEMIE AG


Stress-strain




Stress-strain



Secant modulus-strain



Secant modulus-strain




**Grilon BG-50 S**


PA6-GF50

EMS-GRIVORY | a unit of EMS-CHEMIE AG


**Stress-strain (isochronous) 23°C**




**Creep curve °C**



**Creep modulus-time 23°C**



**Tensile modulus-temperature**



**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Granules

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Chemical Media Resistance**

**Automotive**

Interior

**Electricals & Electronics**









Electrical appliances, Electrical equipment

**Grilon BG-50 S**




PA6-GF50

EMS-GRIVORY | a unit of EMS-CHEMIE AG




**Acids**

-  Acetic Acid (5% by mass) (23°C)
-  Citric Acid solution (10% by mass) (23°C)
-  Lactic Acid (10% by mass) (23°C)
-  Hydrochloric Acid (36% by mass) (23°C)
-  Nitric Acid (40% by mass) (23°C)
-  Sulfuric Acid (38% by mass) (23°C)
-  Sulfuric Acid (5% by mass) (23°C)
-  Chromic Acid solution (40% by mass) (23°C)




**Bases**

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

**Alcohols**

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)


**Hydrocarbons**

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)





**Ketones**

-  Acetone (23°C)










**Ethers**

-  Diethyl ether (23°C)

**Mineral oils**

-  SAE 10W40 multigrade motor oil (23°C)
-  SAE 10W40 multigrade motor oil (130°C)
-  SAE 80/90 hypoid-gear oil (130°C)
-  Insulating Oil (23°C)

**Standard Fuels**






-  ISO 1817 Liquid 1 (60°C)
-  ISO 1817 Liquid 2 (60°C)
-  ISO 1817 Liquid 3 (60°C)
-  ISO 1817 Liquid 4 (60°C)
-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

**Salt solutions**










Grilon BG-50 S

PA6-GF50

EMS-GRIVORY | a unit of EMS-CHEMIE AG

-  Sodium Chloride solution (10% by mass) (23°C)
-  Sodium Hypochlorite solution (10% by mass) (23°C)
-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)
-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethyl Acetate (23°C)
  -  Hydrogen peroxide (23°C)
  -  DOT No. 4 Brake fluid (130°C)
  -  Ethylene Glycol (50% by mass) in water (108°C)
  -  1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
  -  50% Oleic acid + 50% Olive Oil (23°C)
  -  Water (23°C)
  -  Deionized water (90°C)
  -  Phenol solution (5% by mass) (23°C)
-