

Grilon F 47 H NL nat 6020

PA6

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA6, FHS, 32-030/N

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	3000 / 750	MPa	ISO 527-1/-2

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	222 / -	°C	ISO 11357-1/-3

Other properties	dry / cond	Unit	Test Standard
Water absorption	9 / -	%	Sim. to ISO 62
Humidity absorption	3 / -	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183

Film Properties	dry / cond	Unit	Test Standard
Stress at yield (parallel)	35 / -	MPa	ISO 527-3
Stress at yield (normal)	30 / -	MPa	ISO 527-3
Strain at yield (parallel)	15 / -	%	ISO 527-3
Strain at yield (normal)	15 / -	%	ISO 527-3
Maximum strain (parallel)	700 / -	%	ISO 527-3
Maximum strain (normal)	700 / -	%	ISO 527-3
Elmendorf Tear resistance (parallel)	10 / -	N	ISO 6383-2
Elmendorf Tear resistance (normal)	10 / -	N	ISO 6383-2
Trouser Tear resistance (parallel)	30 / -	N/mm	ISO 6383-1
Trouser Tear resistance (normal)	30 / -	N/mm	ISO 6383-1
Dynamic coefficient of friction	0.25 / -	-	ISO 8295
Gloss, 60°	100 / -	-	ISO 2813
WVTR (23°C/85%r.h.)	15 / -	g/(m ² *d)	ISO 15106-1/-2
Oxygen transmission rate (23°C/0%r.h.)	25 / -	cm ³ /(m ² *d*bar)	ISO 15105-1/-2
Oxygen transmission rate (23°C/85%r.h.)	50 / -	cm ³ /(m ² *d*bar)	ISO 15105-1/-2
Carbon Dioxide transm. rate (23°C/0%r.h.)	80 / -	cm ³ /(m ² *d*bar)	ISO 15105-1/-2
Carbon Dioxide transm. rate (23°C/85%r.h.)	250 / -	cm ³ /(m ² *d*bar)	ISO 15105-1/-2
Stress at break (parallel)	100	MPa	ISO 527-3
Stress at break (normal)	90	MPa	ISO 527-3
Gelboflex test	900	holes/m ²	EMS

Rheo/Phys properties	dry / cond	Unit	Test Standard
Melt volume-flow rate (MVR)	15 / -	cm ³ /10min	ISO 1133
Temperature	275 / -	°C	ISO 1133
Load	5 / -	kg	ISO 1133

Characteristics

Processing

Other Extrusion

Delivery form

Granules

Product Attributes

Barrier Properties, High viscosity, Nucleated

Automotive

Automotive electr. and electronics, lighting

Grilon F 47 H NL nat 6020

PA6

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Special Characteristics

Improved heat resistance

Electricals & Electronics

Cables & Tubes

Regional Availability

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa
